



Epoxy Tanking

Code 161 for 5Kg
Code 159 for 5Kg

Grey
White

USE

Epoxy Tanking will provide protection to floors and walls (above and below ground) exposed to aggressive waters severe weather conditions and chemical spillages. and hydrostatic pressure. This product is designed to be used in conjunction with Epoxy Bonding Sealer.

PROPERTIES

The universal 'tanking' product
Easy to use
Waterproof
Wide range of resistance to spillages of Acids, Alkalis and Solvents
Vapour barrier when used in conjunction with Epoxy Bonding Sealer
Virtually odourless

DESCRIPTION

Epoxy Tanking is a two-part Epoxy Resin Coating specially developed for use in most difficult and corrosion resistant areas and can be applied on damp/dry surfaces both internally and externally. This coating is most suitable for application to Factory Floors Walls, Reservoirs, Tanks Swimming Pools, Silos, and Water Treatment Works.

METHOD

PREPARATION OF SUBSTRATE (Essential to adhere to Biokil Crown Tanking Specification)

Before undertaking tanking it is essential that the different types of substrate (e.g. brick, stone, concrete) be identified, because the type and degree of preparation will vary considerably and therefore the costs involved must be carefully calculated. It cannot be emphasised too greatly that **all waterproof coatings entirely rely on the quality of preparation** for their long-term effectiveness and therefore considerable time and expense must be allowed for this work within the job costing.

Please read the Biokil Crown Tanking Specification to ensure correct render backing and tanking systems are being used.

All surfaces should be clean, sound and have no traces of oil grease dust, bitumen or any other contaminant (vacuum cleaning is very important) Concrete laitance should be removed by acid washing and rinsing thoroughly. Cleaning is imperative and best results are obtained by the use of Biokil Crown CONCRETE CLEANER. For best results grit blasting is recommended. It may also be applied to previously painted floors providing they are well abraded or grit blasted vacuumed and sealed with Epoxy Bonding Sealer as loose particles will compromise the bond. Surfaces can be damp but running water must be stopped before Epoxy Bonding Sealer is used (use Mapei Lamposilex water plug) during the application and full curing period. Steel surfaces should be grit blasted to bright metal. In all treatments Epoxy Tanking must be applied over Epoxy Bonding Sealer.

Mixing

First stir the contents of each Pack thoroughly then empty the entire contents of Pack B (small container) into Pack A (large container) taking care to scrape the sides and bottom of the container and stir thoroughly. Continue mixing until the colour is uniform. Up to one litre of clean cold water may be added and mixed thoroughly. Mechanical mixing using a clean paddle attached to a heavy duty slow speed electric drill is recommended. You **MUST** always mix the entire contents of Pack A & B

Application

May be applied when the second coat of Epoxy Bonding Sealer is touch dry but at least within 24 hours. Each coat should be well brushed out to a smooth even finish with the second coat applied at right angles to the first. Do not apply at temperatures below 7°C.

All products supplied by Biokil Crown Ltd are of high quality. The Company however cannot govern the conditions of usage and application of its products and any warrant written or implied covers materials only. The information contained in this leaflet is given in good faith but no liability can be assumed by the Company for any damage, loss or injury or patent infringement arising from its use.



TECHNICAL DATA



NB If Epoxy Bonding Sealer is allowed to cure beyond 24 hours then the first application of Epoxy Tanking may shrink in areas. This will be covered by the second coat but a third coat will be required for full protection. To avoid this problem apply a further coat of Epoxy Bonding Sealer to the cured material before coating with Epoxy Tanking.

Immediately after mixing the material should be applied by brush or airless spray equipment. Two coats are normally required for maximum resistance.

For the best inter coat adhesion the second coat should be applied immediately the first coat is touch dry and within 24 hours after applying the first coat. When using airless spray a dilution of up to 20% with water may be required.

Ensure all equipment is cleaned thoroughly with water. Anti-Slip aggregates are often incorporated in the film to aid additional slip resistance particularly on smooth concrete in wet production areas.

Curing:

Tack free in 24 hours at 20°C. Suitable for light traffic in 24 hours. Full chemical and abrasion resistance in 7 days.

Pot Life:

1-2 hours at 20°C. Reduced pot life at higher temperatures. Extended pot life at lower temperatures

CONTENTS

Epoxy Resin.

COLOURS

Grey, White and Red are sold as standard but most British Standard Colours BS4800 range are available upon request if sufficient quantities are required.

COVERAGE

Up to 30 square metres per 5Kg (single coat to smooth surfaces). Porous surfaces and those with heavy textures will use much more.

PACKAGING

5Kg, Twin Pack labelled

Pack A (Resin) and Pack B (Hardener) combined volume making 5Kg Litres.

SAFETY

As some people find Epoxy Resin based products irritant to the skin all users are recommended to use barrier cream and protective clothing. After use wash hands thoroughly with soap and water. Work to a high standard of personal hygiene. See separate Material Safety Data Sheet. Clean all tools etc., with soap and water immediately after use.

STORAGE & SHELF LIFE

12 months in sealed containers stored at above 5°C. Protect from frost

©HG 08/12 Rev 250615

All products supplied by Biokil Crown Ltd are of high quality. The Company however cannot govern the conditions of usage and application of its products and any warrant written or implied covers materials only. The information contained in this leaflet is given in good faith but no liability can be assumed by the Company for any damage, loss or injury or patent infringement arising from its use.