



GP Building Mastic

Code 929 310ml cartridge Stone
Code 932 310ml cartridge White
Code 933 310ml cartridge Brown
Code 934 310ml cartridge Grey

DESCRIPTION

GP BUILDING MASTIC is an oil based compound intended for general pointing and sealing of many joints in traditional forms of construction. The sealant is rapidly and simply applied by extrusion from a cartridge gun. The product has good adhesion to most clean, dry surfaces.

BENEFITS

Overpaintable..
Adheres to most common surfaces.
Semi drying - remains permanently elastic beneath surface skin.
High solids formulation - excellent gap filling properties without shrinkage.
Good external weathering properties.

AREAS FOR USE

Perimeter pointing internally and externally around doors and windows.
Adheres to concrete, brick, wood, metals and glass without the use of a primer.

LIMITATIONS

Do not use in areas likely to be exposed to solvents, petrols or oils.
Do not apply to fresh concrete or mortar. Allow 28 days to reduce surface alkalinity.
Do not use in conjunction with bitumen or asphalt, Use WEATHER MATE SEALANT.
May stain marble, slate or certain sensitive natural stones.
Do not use on Upvc, polycarbonate or acrylic sheet. Use BUILDING SILICONE.
Do not use in areas where movement exceeds +/- 7.5%.
The product takes 24 -48 hours to skin, but 2-4 weeks to through cure. It should not be used therefore in areas where it is likely to be subjected to interference or damage (eg floor joints). In these cases, use PU SEALANT.

SURFACE PREPARATION

The surfaces to be must be clean, dry and free from dust, grease and other contaminants. New concrete or mortar should be allowed adequate time to dry and mature.

APPLICATION

Joint design should be as follows: Minimum width: 5mm. Maximum width 20mm
Minimum depth : 10mm. Maximum depth: 20mm For deep joints, reduce depth by using FIX AND FILL FOAM or a suitable joint backer rod. All joints should be designed so that the seal is placed in a position which does not retain water or form a water trap. Triangular fillets should be no less than 12mm across the face and should be finished with a flat or convex face.

Cut the tip of the cartridge taking care not to damage the thread. Apply nozzle and cut at an angle of 45° with an opening slightly larger than the gap to be sealed. Apply using a standard sealant gun. Best results will be obtained by keeping an even pressure on the trigger and keeping the gun at a constant angle to the surface being sealed. To ensure a proper bond, always smooth the sealant down with a spatula or piece of wood wetted with linseed oil or white spirits. An improved joint appearance can be achieved by placing masking tape to both sides of the joint, removing within 5 minutes of application.

HEALTH AND SAFETY

GP BUILDING MASTIC is not considered as hazardous to health during normal use. Avoid unnecessary skin contact. Remove with soap and water. If product enters eyes, rinse immediately with soap and water. Seek medical advice if irritation persists.

All products supplied by Biokil Crown Ltd are of high quality. The Company however cannot govern the conditions of usage and application of its products and any warrant written or implied covers materials only. The information contained in this leaflet is given in good faith but no liability can be assumed by the Company for any damage, loss or injury or patent infringement arising from its use.

TECHNICAL DATA



STORAGE

Store in original unopened containers between 15 and 20°C.

SHELF LIFE

12 months from date of manufacture when stored in original unopened containers.

SPECIFIC DATA

FORM Thixotropic paste (ready to use).

APPLICATION TEMP 5°C to 50°C

COVERAGE Approx 10 linear meters per cartridge.

SERVICE TEMP: -25°C to 70°C (90°C intermittent).

CURE

Normally 7 days, the mass below remaining elastic.

SPECIFIC GRAVITY 1.6 approx.

FLASH POINT 65°C

DURABILITY:

Up to 10 years when used as recommended.

SHELF LIFE:

12 months when stored in unopened containers.

COMPATIBILITY

Can be used in contact with most building materials but should not be used against bituminous compounds.

SLUMP:

No slump at 70°C when placed in an 18 x 10mm aluminium channel positioned vertically.

CLEANER White spirits.

UV RESISTANCE

Mechanical properties will not change, however, product may discolour. Overpainting is recommended.

MOVEMENT ACCOM. 7.5% in butt joints, greater in lap joints.

OVERPAINTABILITY

Use conventional decorative paints to increase durability if required.