



Ultraplan

**Ultra-fast hardening
self-levelling compound**



WHERE TO USE

Ultraplan is used for interior levelling and removal of differences in thicknesses from 1 to 10 mm on new or existing substrates, preparing them to receive every type of flooring where a high resistance to loads and traffic is needed. **Ultraplan** is specially suitable for areas set to wheeled-chair traffic.

Ultraplan is for interior use only.

Some application examples

- Levelling concrete slabs and cement screeds or **Topcem**, **Mapecem** or **Topcem Pronto** based screeds.
- Levelling anhydrite substrates.
- Levelling underfloor heating systems.
- Levelling existing floors in concrete, terrazzo, ceramic, natural stone and magnesite.

TECHNICAL CHARACTERISTICS

Ultraplan is a pinkish-grey powder composed of special cements with rapid setting and hydration, graded silica sand, resins and special additives prepared according to a formula developed in the Mapei research laboratories.

Ultraplan mixed with water becomes a fluid and easily workable mortar, perfectly self-levelling, with high bonding strength to the substrate and ultra-fast drying.

Ultraplan can be applied with an automatic pressure pump for distances over 100 m.

Ultraplan can be spread in thicknesses up to 10 mm for each coat without shrinkage, cracking or crazing, and develops very high compressive and flexural strength as well as resistance to indentation and abrasion.

For thicknesses greater than 10 mm (max. 20 mm), it is recommended to add about 30% of graded sand 0/4 mm or gravel 0/8 mm.

Installation of flooring can begin approx. 12 hours after the application of **Ultraplan**, regardless of thickness.

RECOMMENDATIONS

- Do not add more water to a mix that has already started to harden.
- Do not add cement, gypsum plaster or lime to the mix.
- Do not use for exterior levelling work.
- Do not use on substrates subject to continuous rising damp.
- Do not apply an additional coat of **Ultraplan** when the previous one is completely dry; in this case first apply a **Primer G** based primer diluted with 1:3 of water by volume.
- Do not use on metal surfaces.

Ultraplan



Application of Ultraplan with pump and squeegee



Application of Ultraplan with a metal trowel on an existing ceramic tile floor after the application of Mapeprim SP



Detail of the application of Ultraplan on an existing ceramic tile floor after the application of Mapeprim SP

- Do not use **Ultraplan** when the temperature is below +5°C.
- Do not apply **Ultraplan** in thicknesses less than 2 mm if parquet is to be overlaid.

APPLICATION PROCEDURE

Preparing the substrate

The substrates must be solid, dry, free of dust, loose parts, paint, wax, oils, rust and traces of gypsum.

Cement based surfaces that are not sufficiently solid must be removed or where possible consolidated with **Prosfas**, **Primer EP** or **Primer MF**.

Cracks and fissures in the substrate must be repaired with **Eporip**.

In order to fix dust and to provide uniform absorbency of the substrate, dusty or very porous concrete surfaces must be treated with a coat of **Primer G** (1 part **Primer G** with 3 parts of water) or **Livigum** (1 part **Livigum** with 5 parts water).

Anhydrite screeds can be levelled with **Ultraplan** only after the application of a coat of **Primer G**, **Primer S** or **Primer EP**.

On existing ceramic or natural stone surfaces apply a coat of **Mapeprim SP** after the surfaces have been cleaned with detergents and mechanically abraded. Level before **Mapeprim SP** has dried completely (it must still be impressionable).

Preparing the mix

While mixing with a low speed electric mixer, pour a 23 kg bag of **Ultraplan** into a bucket containing 5.5-6 litres of clean water and mix until a uniform lump-free paste is obtained.

More quantities of **Ultraplan** can be prepared in mortar mixers.

After 2-3 minutes of slackening, the mix should be restirred and is then ready for use.

When **Ultraplan** is to be used in thicknesses greater than 10 mm (max. 20 mm), it is recommended to add about 40% graded sand 0/4 mm or 0/8 mm depending on the thicknesses (refer to Mapei Technical Assistance).

The quantity of **Ultraplan** mixed must be used within 20-30 minutes (at a temperature of +23°C).

Applying the mix

Apply **Ultraplan** in a single coat from 1 to 10 mm thick with a large metal trowel or a squeegee, keeping the trowel slightly inclined to obtain the desired thickness.

Ultraplan can also be applied with an automatic pressure pump.

Due to its remarkable self-levelling property, **Ultraplan** immediately eliminates small imperfections (trowel marks, etc.).

If a second coat of **Ultraplan** is required, it is recommended to apply it as soon as the first one is set to light foot traffic (approx. 3 hours at +23°C).

The levelling coat of **Ultraplan** will be ready to receive resilient, carpet, ceramic and wood floor coverings fixed with adhesives after 12 hours at +23°C (time can vary depending on the thickness of the levelling, the room temperature and humidity).

For installing parquet on concrete substrates,



TECHNICAL DATA (typical values)

In compliance with:

– french norms: superior quality levelling compound (P₃) according to UPEC classification

PRODUCT IDENTITY

Consistency:	fine powder
Colour:	pinkish-grey
Specific gravity (g/cm³):	1.3
Dry solids content (%):	100
Storage:	12 months in a dry place in original packing
Hazard classification according to EEC 88/379:	none
Customs class:	3824 50 90

APPLICATION DATA at +23°C - 50% R.H.

Mixing ratio:	24-25 parts water per 100 parts by weight of Ultraplan
Thickness per coat:	from 1 to 10 mm
Self-levelling:	yes
Specific gravity of mix (g/cm³):	1.9
pH of mix:	approx. 12
Application temperature range:	from +5°C to +35°C
Pot life:	20-30 minutes
Setting time:	45-60 minutes
Set to light foot traffic:	3 hours
Waiting time before subsequent bonding:	12 hours

FINAL PERFORMANCES

Compressive strength (N/mm²): – after 1 day: – after 3 days: – after 7 days: – after 28 days:	15.0 19.0 22.0 30.0
Flexural strength (N/mm²): – after 1 day: – after 3 days: – after 7 days: – after 28 days:	3.5 5.5 6.0 8.0
Resistance to abrasion Taber Abrasimeter (Abrading wheel H22-550 g - 200 revolutions) expressed as weight loss: – after 7 days: – after 28 days:	1 g 0.7 g
Brinell hardness (N/mm²): – after 1 day: – after 3 days: – after 7 days: – after 28 days:	60 80 85 110



Taber abrasion executed on Ultraplan (right specimen) and on conventional levelling (left specimen) after 200 cycles



An example of an installation of inlaid PVC on a surface levelled with Ultraplan - CD2 - Milan - Italy



Slab levelled with Ultraplan ready for fixing a floating floor

Ultraplan



the levelling coat of **Ultraplan** must absolutely be at least 3 mm thick. Carefully check the humidity content with a carbide hygrometer or an electric moisture meter, keeping in mind that the latter only gives indicative values.

Cleaning

While it is still fresh **Ultraplan** can be removed from hands and tools with water.

CONSUMPTION

1.6 kg/m² per mm of thickness.

PACKAGING

Ultraplan is available in 23 kg bags.

STORAGE

Stored in a dry place, **Ultraplan** is stable for at least 12 months.

A prolonged storage of **Ultraplan** could, over time, shorten setting time, however without altering its final characteristics.

SAFETY INSTRUCTIONS FOR THE PREPARATION AND APPLICATION

Contains cement, that in contact with sweat or other body fluids produces an irritant alkaline reaction. Use protective gloves and

goggles. For further information consult the safety data sheet.

FOR PROFESSIONALS.

WARNING

N.B. - Although the technical details and recommendations contained in this product report correspond to the best of our knowledge and experience, all the above information must, in every case, be taken as merely indicative and subject to confirmation after long-term practical applications: for this reason, anyone who intends to use the product must ensure beforehand that it is suitable for the envisaged application: in every case, the user alone is fully responsible for any consequences deriving from the use of the product.

All relevant references of the product are available upon request



An example of an installation of wood on a surface levelled with **Ultraplan** - *Messagerie Musicali - Rome - Italy*



An example of an installation of linoleum on a surface levelled with **Ultraplan** - *Monzón Conservatory - Spain*



BUILDING THE FUTURE

MAPEI GROUP CERTIFIED MANAGEMENT SYSTEMS (Quality, Environment and Safety)



MAPEI S.p.A. - ITALY



MAPEI FRANCE



MAPEI INC - CANADA



RESCON MAPEI AS - NORWAY



MAPEI KFT. - HUNGARY



MAPEI FAR EAST Pte Ltd



MAPEI Sro - CZECH REP.