

Technical Data Sheet

<p>General</p> <p>Article number: 90672258</p> <p>Description: 2K Plastic Adhesive Super Fast 30 Seconds (Black) 50 ml</p>	
<p>Specifications 30 Seconds Super-Fast curing. Powerful 2-component (2K-PU) plastic adhesive. For all-purpose structural bonding of plastic parts. Resistant to exposure to elevated temperature, moisture, fuel, many solvents and chemicals. Specially designed for small, quick, durable bonding and repair jobs. Colour Black. Cartridge of 50 ml. Per piece, with 2 mixing tips.</p> <p>Application</p> <ul style="list-style-type: none"> • Small, quick repairs. • Holds parts in position. • Repair a variety of plastic parts. • For instance; Mouldings, bumper tabs, emblems and other basic cosmetic and structural repairs. • In any industry where a fast strong bond is demanded. • Also, excellent bond of many different substrates like plastics, metal, GRP, ceramics, wood etc. <p>Features & Benefits</p> <ul style="list-style-type: none"> • Sandable in 5 minutes! • Excellent adhesion almost all plastics. • No smell. Fast cure. • Superior ambient cure response. • Excellent gap filling properties. • Cure response is NOT depending on the thickness of the applied adhesive as with most other Polyurethane systems. • Easy to sand. • Stays flexible even under cooler conditions. <p>Technical specifications</p> <ul style="list-style-type: none"> • Colour: Black • Packing: 50 ml • Packing unit: 6 pieces per box. • Store: Cool and dry, between +15°C and +32°C; (After opening leave the used mixer tip attached to ensure sealing from humidity, remainder can still be used.) • Shelf life: 24 months • Technical data 	

Open time*:	30 seconds
Handling time*:	2.5 minutes
Sanding time*:	5 minutes
Paint time*:	5 minutes
<i>(* at 23°C)</i>	
Cure	Ambient or heat accelerated cure (max 120°C)
Optimum Bondline Thickness	0.5 mm to 1.5 mm
Maximum Bondline Thickness	± 5 mm
Paint Bake	max 150°C
Tensile strength, MPa @ 23°C	24.8 (ASTM D-638)
Young's Modulus, MPa @ 23°C	1775 (ASTM D-638)
Elongation, %	46 (ASTM D-638)
Shrinkage, %	<1.0 (ASTM C-733)

Substrate Range

Substrate	Surface preparation	General Adhesion
SMC, BMC, RTM, Gel Coat, Wood, HPL, PUR-RIM	Sanding	Excellent
Carbon Fiber Reinforced Plastics (CFRP)	Sanding or peel ply	Excellent
Coated or primed Metals and Metal alloys**	None	Excellent
HLU (Hand lay up) , HSU (Hand spray up)	Sanding	Good
Thermoplastics A (ABS, PA, PC/PBT, PPO/PA, PET)	Sanding or solvent wipe	Very Good
Thermoplastics B (PPO, PC/ABS, PP/EPDM)	Solvent, detergent or primer	Good / Fair
Thermoplastics C (PTFE, PP, PE, PVC, PPS, POM)	Physical pre-treatment (flame, plasma, corona)	Limited

Substrate Preparation and processing.

- The surface has to be clean, and free of dust, oil and grease.
- Attach the Mixer Tip on top.
- Press out some product (± 25 – 50 mm) To make sure that the product is properly mixed.
- Pull the trigger of the 2K Manual Gun at a constant force for an even layer of adhesive.
- Make sure that the top of the Mixer Tip is always in the product, this prevents air from enclosing in the adhesive. Which will form air bubbles when applied.
- When cured (read technical information) sand and refinish when needed.
- After finishing leave the mixer tip in place.
- When using again, remove the mixer tip. Carefully clean the cartridge nozzle. (The products in the two chambers must be cleanly separated.) Attach a new mixer tip and start a new job.

Paintability.

Paintable with the most car repair 1K and 2K paints. Due to the diversity of varnishes and paints we recommend preliminary tests.

Related products Colad

Article number: 90672666

Description: Gun for 2K Plastic Adhesive Manual

Article number: 90672980/90672981

Description: Mixing Tips Plastic Repair

Disclaimer Technical Data Sheet & Material Safety Data Sheet

It is the responsibility of the user to read understands and apply the information of the TDS. The information about work and environmental safety is available on the material safety data sheet via www.colad.co. It is the responsibility of the user to read and apply the information.

Notice

Products are for professional use. The adhesive could be harmful if improperly handled. Contact with skin and eyes should be avoided and necessary protective equipment and clothing should be worn.

The repairs should always be done in accordance with the OEM rules and specifications.

All information is for the user's consideration, investigation and verification. The specific use applications and conditions of use are beyond the control of EMM International B.V.. It is the responsibility of the user to determine the suitability of any of the products mentioned for the user's specific application.

Created by:

EMM International BV

Bohemestraat 19, 8028 SB Zwolle, The Netherlands

www.emm.com



T +31(0)38 467 66 00

www.colad.co