

WORK MATERIAL	NON-ALLOY STEELS		ALLOY STEELS		SOFT GREY CAST IRON		HARD GREY CAST IRON	
STRENGTH	< 700 N/mm <sup>2</sup>		< 1000 N/mm <sup>2</sup>		< HB240, GG25		< HB300, GG40	
DIAMETER	N	S	N	S	N	S	N	S
1.0	13000	0.04	11250	0.04	21300	0.04	14200	0.04
2.0	13000	0.06	11250	0.06	21300	0.06	14200	0.06
3.0	13000	0.13	11000	0.13	21000	0.13	14000	0.13
4.0	9500	0.14	8400	0.14	16000	0.14	10500	0.14
5.0	7600	0.15	6700	0.15	13000	0.15	8300	0.15
6.0	6400	0.17	5600	0.17	11000	0.17	6900	0.17
7.0	5500	0.19	4800	0.19	9100	0.19	5900	0.19
8.0	4800	0.21	4200	0.21	8000	0.21	5200	0.21
9.0	4200	0.23	3700	0.23	7100	0.23	4600	0.23
10.0	3800	0.25	3350	0.25	6400	0.25	4150	0.25
12.0	3200	0.27	2800	0.27	5300	0.27	3450	0.27
14.0	2750	0.29	2400	0.29	4550	0.29	3000	0.29
16.0	2400	0.31	2100	0.31	4000	0.31	2600	0.31
18.0	2100	0.33	1850	0.33	3550	0.33	2300	0.33
20.0	1900	0.35	1650	0.35	3200	0.35	2100	0.35