

Tubing



- Nylon, Polyurethane and Polyolefin Tubing
- Standard and Metric Sizes Available
- Different Types for Various Applications
- Multitude of Color Choices

SMC is widely recognized as a world leader in motion automation technology. Our worldwide reputation for quality and reliability was earned through our commitment to research and development, engineering, sales support, and customer service. We are truly a global company with a local focus to ensure our customers needs are met wherever their business takes them.

We offer a comprehensive line of technologically advanced products. This product offering now includes a tubing product line that was developed and manufactured to meet SMC's strict quality standards. 12 different types of tubing for general industrial applications are offered as well as D.O.T. tubing and tubing made of Teflon[®].

To address the different needs of industry, we offer Nylon and Polyolefin tubing in at least 2 different hardness ratings, and our Polyurethane tubing is available in 4 hardness ratings. To maintain the highest quality possible, the outside diameter as well as the wall thickness of SMC tubing are inspected during the manufacturing process for dimensional accuracy.

If your application happens to be spot welding, clean room, robotics, heavy vehicle or motion automation, SMC not only has the right tubing, but also offers it in Standard and Metric sizes in a multitude of colors. Contact your SMC representative at 1-800-SMC-SMC1 or visit us on the worldwide web at www.smcusa.com.



SMC is widely recognized as a world leader in motion automation technology.





Table Of Contents

Nylon Tubing Information	
Series TIA	
Series T	
Series TS/TISA	
Polyurethane Tubing Information8	
Series TIUB	
Series TU	
Series TUS	
Series TUH - Standard Pressure12	
Series TUH - High Pressure	
Series TCU	
Series TFU	
Clean Series Tubing 10-TU, 10-TCU, 10-TFU	
Polyolefin Tubing, Series TPH, TPS17	
Antistatic Tubing Series TAS	
Antistatic Tubing Series TAU	
Flame Resistant Series TIRS/TRS 20	
Flame Resistant Series TRB	
Flame Resistant Series TRBU 22	
How To Install TRB/TRBU Tubing	
Accessories Series TM, TG	
Accessories Series TK, TKS, TB-3VS	
Chemical Resistance Chart - Nylon 12 26	
Chemical Resistance Chart - Polyurethane	
Chemical Resistance Chart - Polyolefin	
Safety Instructions	
Precautions	
Custom Options	

Nylon Tubing

Nylon was developed more than half a century ago and is considered to be the first man-made thermoplastic available. Deemed a rugged engineering plastic, its properties make it an ideal choice for a variety of applications. Nylon does not depend on moisture for flexibility and will not become brittle or swell because of water. therefore, it has excellent low moisture absorption and dimensional stability characteristics.



Nylon tubing for pneumatic applications is made from Nylon 11, and more recently Nylon 12. Nylon 12 has virtually the same physical properties and performance as Nylon 11.

SMC mainly uses Nylon 12. Nylon 11 is offered by request.

Properties

- ▲ Dimensional stability
- ▲ Low moisture absorption
- Elastic memory
- ▲ High impact resistance
- High thermal resistance

- ▲ Light weight
- ▲ Wide temperature range
- ▲ High abrasion resistance
- ▲ Good flexibility
- Broad chemical resistance



For general use



Dimensions

Inch	Serie	es TIA					
Model	TIA01		TIA05	TIA07		TIA11	TIA13
Tube OD (Inches)	1/8	5/32	3/16	1/4	5/16	3/8	1/2
Tube ID (Inches)	0.086	0.098	0.137	0.18	0.236	0.275	0.378
Min. bending radius (Inches)	0.59	0.51	0.79	1.18	1.89	2.36	2.95

*For 5/32 and 5/16 tubing, please refer to 4mm (T0425) and 8mm (T0806) tubing on page 6.

Specifications

Operating Fluid	Air, Water
Max. Operating Pressure	220 psi (1.5MPa) at 68°F (20°C)
Burst Pressure	Refer to burst pressure characteristic chart
Operating Temperature	Air: -4° to 140°F (-20° to 60°C)
	Water: 40° to 105°F (5° to 40°C)
Material	Nylon 12
Hardness	Shore D 70

Burst Pressure Characteristics Chart



How To Order



Note* - For 5/32 and 5/16 size tubing, please refer to 4mm (T0425) and 8mm (T0806) "How to Order" information on page 6

A Caution

- 1. Can be used with general industrial water. For other fluids, please consult SMC.
- 2. Max. operating pressure and minimum bending radius are measured at 68°F.
- 3. When using tubing with SMC fittings, the chemical resistance of the fitting has to be investigated as well.

Packaging Design					Inch	Size	Tubing
Length	1/8	5/32	3/16	1/4	5/16	3/8	1/2
100ft	Bag	Refer to	Bag	Bag	Refer to	Bag	Bag
500ft	Bag	4mm	Bag	Bag	8mm	Reel	Reel
1000ft	Reel	Tubing	Reel	Reel	Tubing	Reel	Reel

Nylon Tubing

For general use



Dimensions

Metric	Serie	es T						
Model	T0425	T0403	T0604	T0645	T0806	T1075	T1209	T1613
Tube OD (mm)	4	4	6	6	8	10	12	16
Tube ID (mm)	2.5	3	4	4.5	6	7.5	9	13
Min. bending radius (mm)	13	25	24	36	48	60	75	100

Specifications

Operating Fluid	Air, Water
Max. Operating Pressure	220 psi (1.5MPa) at 68°F (20°C)
Burst Pressure	Refer to burst pressure characteristic chart
Operating Temperature	Air: -4° to 140°F (-20° to 60°C)
	Water: 40° to 105°F (5° to 40°C)
Material	Nylon 12
Hardness	Shore D 70

Burst Pressure Characteristics Chart



▲ Caution

- 1. Can be used with general industrial water. For other fluids, please consult SMC.
- 2. Max. operating pressure and minimum bending radius are measured at 68°F.
- **3.** When using tubing with SMC fittings, the chemical resistance of the fitting has to be investigated as well.

How To Order

Nylon —	Metric Size	0604		tion	20 Length Per	Boll
	Symbol	Tube Size	Symbol	Color	Symbol	Roll Size
	0425	4mm (5/32")	В	Black	20	20m
	0403	4mm	W	White	100	100m
	0604	6mm	R	Red	l onger leng	ths available
	0645	6mm	BU	Blue	upon reques	
	0806	8mm (5/16")	Y	Yellow		
	1075	10mm	G	Green		
	1209	12mm				
	1613	16mm				

Packaging Design				Metrie	c Size	Tubing
Length	4mm	6mm	8mm	10mm	12mm	16mm
20m	Bag	Bag	Bag	Bag	Bag	Bag
100m	Bag	Bag	Bag	Box	Box	Reel

Series TS, TISA

Soft Nylon Tubing

All-purpose tubing using soft Nylon compound for added flexibility



Burst Pressure Characteristics Chart



$riangle extsf{ } ext$

- 1. Do not use with general industrial water. Water will cause the O.D. to shrink, which could cause leaks or the possible release of the tubing from the one-touch® fitting.
- 2. Max. operating pressure and minimum bending radius are measured at 68°F.
- **3.** When using tubing with SMC fittings, the chemical resistance of the fitting has to be investigated as well.

Dimensions

Inch	Series TISA									
Model	TISA01		TISA05	TISA07		TISA11	TISA13			
Tube OD (Inches)	1/8	5/32	3/16	1/4	5/16	3/8	1/2			
Tube ID (Inches)	0.086	0.098	0.137	0.18	0.236	0.275	0.378			
Min. bending radius (Inches)	0.47	0.47	0.59	0.91	0.91	1.18	1.57			
*For 5/32 and 5/16 tubing, please refer to 4mm and 8mm tubing.										

'16 tubing, please refer to 4mm and 8mm tubi

Metric	Series TS						
Model	TS0425	TS0604	TS0806	TS1075	TS1209	TS1612	
Tube OD (mm)	4	6	8	10	12	16	
Tube ID (mm)	2.5	4	6	7.5	9	12	
Min. bending radius (mm)	12	15	23	27	31	60	

Specifications

-	
Operating Fluid	Air
Max. Operating Pressure	145 psi (1MPa) at 68°F (20°C)
Burst Pressure	Refer to burst pressure characteristic chart
Operating Temperature	-4° to 140°F (-20° to 60°C)
Material	Nylon 12
Hardness	Shore D 56

How To Order

	<u>tisa</u>	0	7	B	-
Soft • Nylon	Inch Size			Color Indica	tion
	Symbol	Tube Size		Symbol	Color
	01	1/8		В	Black
	See Note*	5/32		W	White
	05	3/16		R	Red
	07	1/4		BU	Blue
	See Note*	5/16		Y	Yellow
	11	3/8		G	Green
	13	1/2			
	Note* - For	5/32 and \$	5/16 siz	e tubing, ple	ase refer

1]	

Length Per Roll

Symbol	Roll Size					
20	20m					
100	100m*					
Longer longthe evolution						

Longer lengths available upon request

*Black & White Only

refer to 4mm and 8mm "How to Order" information

Soft •	<u>TS</u>	<u>0604</u>	W	-
Nylon	Metric Size		Color Indica	tion
	Symbol	Tube Size	Symbol	Color
	0425	4mm	В	Black
	0604	6mm	W	White
	0806	8mm	R	Red
	1075	10mm	BU	Blue
	1209	12mm	Y	Yellow
	1612	16mm	G	Green

1	0	0
_		

Length Per Roll							
Symbol	Roll Size						
20	20m						
100	100m*						

Longer lengths available upon request

*Black & White Only

Packaging Design Inch Size Tubing									
Length	1/8	5/32	3/16	1/4	5/16	3/8	1/2		
20m	Bag	Refer to	Bag	Bag	Refer to	Bag	Bag		
100m	Reel	4mm	Reel	Reel	8mm	Reel	Reel		

Packaging Design				Metrie	c Size	Tubing
Length	4mm	6mm	8mm	10mm	12mm	16mm
20m	Bag	Bag	Bag	Bag	Bag	Bag
100m	Bag	Bag	Bag	Box	Box	Reel

Polyurethane Tubing

Polyurethane tubing is fast becoming the ideal choice for pneumatic applications. It combines the elasticity of rubber with the chemical resistance normally reserved for plastics. Polyurethane can be put into two classifications, ester based and ether based. SMC offers both.

Ether based polyurethane is the preferred tubing material for general pneumatic applications due to its immunity to hydrolysis and its higher resistance to fungus and microorganism attacks. The Ester based polyurethane is a stronger compound but tends to hydrolyze with moisture. This hydrolysis process will degrade the material over time.



SMC's primary line of polyurethane tubing is ether based, made from the highest quality compound available, to ensure the longest tubing life. The ester based TUH series is the exception. This product line was developed to take advantage of the greater strength offered by this compound.

Properties

- Cut resistant
- Excellent memory
- Wide temperature range
- Low compression set
- Low gas permeability

- Kink resistant
- Tear resistant
- Abrasion resistant
- ▲ Extreme flexibility
- ▲ Good chemical resistance



For general use



Dimensions

Inch	Serie	s TIU	В				
Model	TIUB01		TIUB05	TIUB07		TIUB11	TIUB13
Tube OD (Inches)	1/8	5/32	3/16	1/4	5/16	3/8	1/2
Tube ID (Inches)	0.08	0.1	0.13	0.17	0.2	0.25	0.33
Min. bending radius (Inches)	0.39	0.39	0.6	0.91	0.79	1.06	1.38

*For 5/32 and 5/16 tubing, please refer to 4mm and 8mm tubing on page 10.

Specifications

Operating Fluid	Air, Water
Max. Operating Pressure	115 psi (0.8MPa) at 68°F (20°C)
Burst Pressure	Refer to burst pressure characteristic chart
Operating Temperature	Air: -4° to 140°F (-20° to 60°C)
	Water: 40° to 105°F (5° to 40°C)
Material	Polyurethane
Hardness	Shore A 95

Burst Pressure Characteristics Chart



How To Order

	<u>TIUB</u>	<u>05</u>		BU	-	<u>33</u>	
Polyurethan			-1				
	Inch Size			Color Indica	tion 🌡	Length Per	Roll
	Symbol	Tube Size		Symbol	Color	Symbol	Roll Size
	01	1/8		В	Black	20	66ft
	See Note*	5/32		W	White	33 ¹	100ft
	05	3/16		R	Red	1531	500ft
	07	1/4		BU	Blue	305 ¹	1000ft
	See Note*	5/16		Y	Yellow	Longer leng	ths available
	11	3/8		G	Green	upon reques	
	13	1/2		С	Clear	¹ Stocked ite	m
				YR	Orange		,,,,,

Note* - For 5/32 and 5/16 size tubing, please refer to 4mm and 8mm "How to Order" information on page 10.

* - Quick ship colors indicated, see chart on page 31 for other available colors

\triangle Caution

- 1. Can be used with general industrial water. For other fluids, please consult SMC.
- 2. Max. operating pressure and minimum bending radius are measured at 68°F.
- 3. When using tubing with SMC fittings, the chemical resistance of the fitting has to be investigated as well.

Packaging Design					Inch	Size	Tubing
Length	1/8	5/32	3/16	1/4	5/16	3/8	1/2
66ft	Bag	Refer to	Bag	Bag	Refer to	Bag	Bag
100ft	Bag	4mm	Bag	Bag	8mm	Reel	Reel
500ft	Bag	tubing	Bag	Bag	tubing	Reel	Reel
1000ft	Reel		Reel	Reel		Reel	Reel

For general use



Dimensions

Metric	ic Series TU							
Model	TU0425	TU0604	TU0805	TU1065	TU1208			
Tube OD (mm)	4	6	8	10	12			
Tube ID (mm)	2.5	4	5	6.5	8			
Min. bending radius (mm)	10	15	20	27	35			

Specifications

Operating Fluid	Air, Water
Max. Operating Pressure	115 psi (0.8MPa) at 68°F (20°C)
Burst Pressure	Refer to burst pressure characteristic chart
Operating Temperature	Air: -4° to 140°F (-20° to 60°C)
	Water: 40° to 105°F (5° to 40°C)
Material	Polyurethane
Hardness	Shore A 95

Burst Pressure Characteristics Chart



How To Order

Polyuretha	Metric Size	060	-		tion	20 Length Per	Roll
	Symbol	Tube Size		Symbol	Color	Symbol	Roll Size
	0425	4mm (5/32")		В	Black	20 ¹	20m
	0604	6mm		W	White	33	33m
	0805	8mm (5/16")		R	Red	100 ¹	100m
	1065	10mm		BU	Blue	153	153m
	1208	12mm		Y	Yellow	305	305m
				G	Green	500 ¹	500m*
				С	Clear	Longer leng	ths available
				YR	Orange	upon reques	st

¹Stocked item

* 4mm, 6mm, 8mm

* - Quick ship colors indicated, see chart on page 31 for other available colors

Packaging Design			Metric	Size	Tubing
Length	4mm	6mm	8mm	10mm	12mm
20m	Bag	Bag	Bag	Bag	Bag
33m	Bag	_	Bag	_	
100m	Bag	Bag	Bag	Box	Box
153m	Bag	_	Box	_	_
305m	Reel	—	Reel	—	_
500m	Reel	Reel	Reel	_	_

⚠ Caution

- 1. Can be used with general industrial water. For other fluids please consult SMC.
- 2. Max. operating pressure and minimum bending radius are measured at 68°F.
- **3.** When using tubing with SMC fittings, the chemical resistance of the fitting has to be investigated as well.

Series TUS

Soft Polyurethane Tubing

Suitable for environments where extreme flexibility is required



Burst Pressure Characteristics Chart



Dimensions

Metric Series TUS							
Model	TUS0425	TUS0604	TUS0805	TUS1065	TUS1208		
Tube OD (mm)	4	6	8	10	12		
Tube ID (mm)	2.5	4	5	6.5	8		
Min. bending radius (mm)	8	15	15	22	29		

Specifications

-	
Operating Fluid	Air
Max. Operating Pressure	87 psi (0.6MPa) at 68°F (20°C)
Burst Pressure	Refer to burst pressure characteristic curve
Operating Temperature	-4° to 140°F (-20° to +60°C)
Material	Polyurethane
Hardness	Shore A 89

How To Order



Packaging Design			Metric	Size	Tubing
Length	4mm	6mm	8mm	10mm	12mm
20m	Bag	Bag	Bag	Bag	Bag
100m	Reel	Reel	Reel	Reel	Reel

Series TJ Inner Sleeve TUS related accessories

Reinforces soft polyurethane tubing. Insert an inner sleeve into the end of soft polyurethane tubing when used with a One-Touch[™] fitting.



Model

Part No.	Applicable Tube Model	Length
TJ-0425	TUS0425	18
TJ-0604	TUS0604	19
TJ-0805	TUS0805	20.5
TJ-1065	TUS1065	23
TJ-1208	TUS1208	24

Specifications

Material	C2700T (Electroless nickel plating
Wall thickness	0.2mm

⚠ Caution

- **1.** Do not use with general industrial water.
- 2. Max. operating pressure and minimum bending radius are measured at 68°F.
- **3.** When using tubing with SMC fittings, the chemical resistance of the fitting has to be investigated as well.
- **4.** Always use inner sleeve (Series TJ) in safety circuit or critical area.

Hard Polyurethane Tubing

Standard

Increased flow capability as compared to SMC's standard polyurethane tubing



Burst Pressure Characteristics Chart



Dimensions

Metric	Series TUH					
Model	TUH0428	TUH0644	TUH0858	TUH1073	TUH1288	
Tube OD (mm)	4	6	8	10	12	
Tube ID (mm)	2.8	4.4	5.8	7.3	8.8	
Min. bending radius (mm)	10	18	24	30	36	

Specifications

Operating Fluid	Air
Max. Operating Pressure	115 psi (0.8MPa) at 68°F (20°C)
Burst Pressure	Refer to burst pressure characteristic chart
Operating Temperature	-4° to 140°F (-20° to 60°C)
Material	Polyurethane
Hardness	Shore D 57

Note) Cannot be used for water due to the occurrence of hydrolysis.



Packaging Design Metric Size Tubing						
Length	4mm	6mm	8mm	10mm	12mm	
20m	Bag	Bag	Bag	Bag	Bag	
100m	Bag	Bag	Bag	Box	Box	

⚠ Caution

- 1. Do not use with general industrial water due to the occurrence of hydrolysis.
- 2. Max. operating pressure and minimum bending radius are measured at 68°F.
- **3.** When using tubing with SMC fittings, the chemical resistance of the fitting has to be investigated as well.



Bend the tube into U-form at a temperature of 68°F. Fix one end and close loop gradually. Measure 2R when the tubing starts to kink.

Hard Polyurethane Tubing

High Pressure

Operating pressure is 25% higher than standard TUH tubing



Burst Pressure Characteristics Chart



\land Caution

- 1. Do not use with general industrial water due to the occurrence of hydrolysis.
- 2. Max. operating pressure and minimum bending radius are measured at 68°F.
- **3.** When using tubing with SMC fittings, the chemical resistance of the fitting has to be investigated as well.

Dimensions

Metric Series TUH					
Model	TUH0425	TUH0604	TUH0805	TUH1065	TUH1208
Tube OD (mm)	4	6	8	10	12
Tube ID (mm)	2.5	4	5	6.5	8
Min. bending radius (mm)	10	15	20	27	35

Specifications

Operating Fluid	Air
Max. Operating Pressure	145 psi (1.0MPa) at 68°F (20°C)
Burst Pressure	Refer to burst pressure characteristic chart
Operating Temperature	-4° to 140°F (-20° to 60°C)
Material	Polyurethane
Hardness	Shore D 57

BU

Note) Can not be used for water due to the occurrence of hydrolysis

How To Order



Metric Size	Color India	
Symbol	Tube Size	Symbol
0425	4mm	В
0604	6mm	W
0805	8mm	BU
1065	10mm	N
1208	12mm	

0604

lor Indication							
symbol Color							
В	Black						
W	White						
BU	Blue						
Ν	Translucent						

Length Per Roll							
Symbol Roll Size							
20	20m						
100 100m							
Longer leng	the available						

100

Longer lengths available upon request

Packaging Design			Metric	Size	Tubing
Length	4mm	6mm	8mm	10mm	12mm
20m	Bag	Bag	Bag	Bag	Bag
100m	Bag	Bag	Bag	Box	Box



Bend the tube into U-form at a temperature of 68°F. Fix one end and close loop gradually. Measure 2R when the tubing starts to kink.

Polyurethane Coil Tubing

Series TCU

Ideal for use with robotics and pneumatic pick and place applications



Burst Pressure Characteristics Chart





*Dimensions subject to change due to material

\land Caution

- 1. Contact SMC regarding other fluids.
- 2. Max. operating pressure and minimum bending radius are measured at 68°F.
- **3.** When using tubing with SMC fittings, the chemical resistance of the fitting has to be investigated as well.

Dimensions

Metric	Series TCU						
Model	TCU 0425B-1	TCU 0425B-2	TCU 0425B-3	TCU 0604B-1	TCU 0604B-2	TCU 0604B-3	TCU 0805B-1
Number of Tubes	1	2	3	1	2	3	1
Tube OD (mm)	4	4	4	6	6	6	8
Tube ID (mm)	2.5	2.5	2.5	4	4	4	5

Specifications

Operating Fluid	Air
Max. Operating Pressure	115 psi (0.8MPa) at 68°F (20°C)
Burst Pressure	Refer to burst pressure characteristic chart
Operating Temperature	-4° to 140°F (-20° to 60°C)
Material	Polyurethane
Hardness	Shore A 95

How To Order



2Number of TubesSymbolNumber
of Tubes112233

Coil Dimensions

Specifications

Davit Na	Tube Size (mm)		Dimension	Dimension of Coil (mm)		Number of Coil Windings	Maximum Operating	
Part No.	0.D.	I.D.	L	ØD	of Tubes	of Coil Windings Per Tube Length	Length (m)	
TCU0425B-1			210	18	1	52	1.5	
TCU0425B-2	4	2.5	280 28		2	35	1.5	
TCU0425B-3			265	20	3	22	1	
TCU0604B-1			325	24	1	54	2	
TCU0604B-2	6	4		37	2	27	1.5	
TCU0604B-3			305	57	3	17	1	
TCU0805B-1	8	5	330	31	1	41	2	

Made To Order

Consult SMC for detailed specifications, dimensions and delivery.

Change of Coil Turns / Color Change

Part No.	Tube Siz O.D.	ze (mm) I.D.	Dimension (of Coil (mm) ØD	Number of Tubes	Number of Coil Windings Per Tube Length	Maximum Operating Length (mm)		
TCU0425 -1-N-X6	-		N X 4	18	1	3 to 90	LX5.9+200		
TCU0425 -2-N-X6	4	2.5	N X 8	28	2	3 to 90	LX4.4+200		
TCU0425 - 3-N-X6			N X 12	28	3	3 to 63	LX2.9+200		
TCU0604 -1-N-X6			N X 6	24	1	3 to 90	LX5.3+200		
TCU0604 -2-N-X6	6	4	N X 12	37	2	3 to 66	LX3.8+200		
TCU0604 - 3-N-X6			N X 18	37	3	3 to 44	LX2.5+200		
TCU0805 -1-N-X6	8	5	N X 8	31	1	3 to 90	LX5.2+200		
TCU0805 -2-N-X6	0	5	N X 16	42	2	3 to 40	LX3+200		
TCU1065 -1-N-X6	10	6.5	N X 10	52	1	3 to 45	LX5+200		
TCU1065 -2-N-X6	10	10 6.5	N X 20	52	2	3 to 35	LX3+200		
TCU1208 -1-N-X6	12	8	N X 12	67	1	3 to 35	LX5+200		
TCU1208 -2-N-X6	12	0	N X 24	67	2	3 to 30	LX3+200		

🗇 = B (Black), W (White), R (Red), BU (Blue), Y (Yellow), G (Green), C (Clear), YR (Orange)

*L is calculated by the number of coils (N) X O.D.

Series TFU

Polyurethane Flat Tubing

Eliminates the need for jacketing or spiral wrapping of multiple tubes





Burst Pressure Characteristics Chart



⚠ Caution

- 1. Contact SMC regarding other fluids.
- Max. operating pressure is measured at 68°F.
- **3.** When using tubing with SMC fittings, the chemical resistance of the fitting has to be investigated as well.

Dimensions

Metric	Series	TFU				
Model	TFU	TFU	TFU	TFU	TFU	TFU
Woder	0425B-2	0425B-3	0604B-2	0604B-3	0805B-2	0805B-3
Number of Tubes	2	3	2	3	2	3
Tube OD (mm)	4	4	6	6	8	8
Tube ID (mm)	2.5	2.5	4	4	5	5

Specifications

Operating Fluid	Air
Max. Operating Pressure	115 psi (0.8MPa) at 68°F (20°C)
Burst Pressure	Refer to burst pressure characteristic chart
Operating Temperature	-4° to 140°F (-20° to 60°C)
Material	Polyurethane
Hardness	Shore A 95



Made to Order

Consult SMC for detailed specifications, dimensions and delivery.

Мо	del	TFU0425 🗖	TFU0604 🗖	TFU0805 🗖	TFU1065 🗖	TFU1208 🗖
Tube	0.D.	4	6	8	10	12
Tube	e I.D.	2.5	4	5	6.5	8
Number of Tubes	2 3 4 5 6 7 8					

• : 10m roll

Suffix "X3" to the end of the part

TFU0425BU-3-100- X3

Ex.) TFU0425B-2-50-X3,

number.

: 100m roll

1. Color Change (10m roll)

Suffix "X4" to the end of the part number. Ex.) TFU0604BU-2-10-[X4] Note) W: White, R: Red, BU: Blue, Y: Yellow, G: Green, C: Transparent, YR: Orange (All tubes are same color) 2. Longer roll length (50m or 100m roll)

3. Number of Tubes (10m roll)

Suffix "X4" to the end of the part number. Ex.) TFU0604B-4-10-X4, TFU0604YR-4-10- X4

 \triangle : 50m roll

Clean Series Tubing

Polyurethane Tubing

How To Order



Color Indication

Symbol Color

Black

White

Red

Blue

Yellow

Green

Clear

Orange

В

W

R

BU

Y

G

С

YR

Length Per Roll

20

Symbol Roll Size

20m

Dimensions

Metric	Series	TU			
Model	10-TU0425	10-TU0604	10-TU0805	10-TU1065	10-TU1208
Tube OD (mm)	4	6	8	10	12
Tube ID (mm)	2.5	4	5	6.5	8
Min. bending radius (mm)	10	15	20	27	35

Series 10-TU

Series 10-TCU

Series 10-TFU

Snecifications

opoonioutiono	
Operating Fluid	Air, Water
Max. Operating Pressure	115 psi (0.8MPa) at 68°F (20°C)
Burst Pressure	Refer to burst pressure characteristic chart
Operating Temperature	Air: -4° to 140°F (-20° to 60°C)
	Water: 40° to 105°F (5° to 40°C)
Material	Polyurethane
Hardness	Shore A 95

Polyurethane Coiled Tubing

How To Order TCU 0425 10 В Clean Color Indication Number of Tubes Series Number Symbol Color Symbol Metric Size of Tubes Tube В Black 1 **Symbol** 1 Size 2 2 0425 4mm 3 3 0604 6mm 0805 8mm

Dimensions Metric **Series TCU** 10-TCU 10-TCU 10-TCU 10-TCU 10-TCU 10-TCU 10-TCU Model 0425B-1 0425B-2 0425B-3 0604B-1 0604B-2 0604B-3 0805B-1 Number of tubes 1 2 3 2 3 1 1 Tube OD (mm) 4 4 4 6 6 6 8 Tube ID (mm) 2.5 2.5 2.5 4 4 4 5

Specifications

•	
Operating Fluid	Air
Max. Operating Pressure	115 psi (0.9MPa) at 68°F (20°C)
Burst Pressure	Refer to burst pressure characteristic chart
Operating Temperature	-4° to 140°F (-20° to 60°C)
Material	Polyurethane
Hardness	Shore A 95



Polyurethane Flat Tubing

How To Order

Cle	10 -	TFI		425	B –	2 of Tubes
Se	ries Metric Siz	ze	Symbol		Symbol	Number
	Symbol	Tube	В	Black	2	2
	-	Size			3	3
	0425	4mm				
	0604	6mm				
	0805	8mm		T		
					ST.	

Dimoneione

DIIIGII9I0II9						
Metric	Series	s TFU				
Model	10-TFU 0425B-2	10-TFU 0425B-3	10-TFU 0604B-2	10-TFU 0604B-3		10-TFU 0805B-3
Number of tubes	2	3	2	3	2	3
Tube OD (mm)	4	4	6	6	8	8
Tube ID (mm)	2.5	2.5	4	4	5	5

Specifications

••••••	
Operating Fluid	Air
Max. Operating Pressure	115 psi (0.9MPa) at 68°F (20°C)
Burst Pressure	Refer to burst pressure characteristic chart
Operating Temperature	-4° to 140°F (-20° to 60°C)
Material	Polyurethane
Hardness	Shore A 95

16

Symbol

Series

Metric Size

0425

0604

0805

1065

1208

Tube

Size

4mm

6mm

8mm

10mm

12mm

Series TPH / TPS

Designed to be used for blow-off and washing lines in clean room environments





Dimensions

Metric	Series	ТРН			
Model	TPH0425	TPH0604	TPH0806	TPH1075	TPH1209
Tube OD (mm)	4	6	8	10	12
Tube ID (mm)	2.5	4	6	7.5	9
Min. bending radius (mm)	15	25	35	45	55

Specifications

Operating Fluid	Air, Nitrogen, Pure Water
Max. Operating Pressure	145 psi (1.0MPa) at 68°F (20°C) for 4mm & 6mm tubing
Max. Operating Pressure	101 psi (0.7MPa) at 68°F (20°C) for other diameter tubing
Burst Pressure	Refer to burst pressure characteristic chart
Operating Temperature	Air: -4° to 176°F (-20° to 80°C) Water: 40° to 176°F (5° to 80°C)
Material	Polyolefin
Hardness	Shore D 59

How To Order

	TPH	0604	4	B	-		100	
Polyolefin -	Metric Size		Color	Indicat	ion	-		
		-	00.01				Length Per	Roll
	Symbol	Tube Size	Syr	nbol	Color		Symbol	Roll Size
	0425	4mm		B	Black			
	0604	6mm	1	W	White		20	20m
	0806	8mm		R	Red		100	100m
	1075	10mm	E	3U	Blue		Longorlong	
	1209	12mm		Y	Yellow			ths available
				G	Green	upon request		51
Packaging Design Metric Size Tubing								
	Leng	th	4mm	6mm	8mm	10m	m 12mm	
20m		Bag	Bag	Bag	Ва	g Bag		
]	100r	n	Bag	Bag	Bag	Ва	g Bag	

Soft Polyolefin

Burst Pressure Characteristics Chart



🗥 Caution

1. Contact SMC regarding other fluids.

- 2. Max. operating pressure and minimum bending radius are measured at 68°F.
- **3.** When using tubing with SMC fittings, the chemical resistance of the fitting has to be investigated as well.

Dimensions

Series TPS Metric Model TPS0425 **TPS0604 TPS0805** TPS1065 TPS1208 Tube OD (mm) 4 6 8 10 12 Tube ID (mm) 2.5 5 6.5 8 4 Min. bending radius (mm) 10 20 25 30 40

Specifications

Operating Fluid	Air, Nitrogen, Pure Water
Max. Operating Pressure	101 psi (0.7MPa) at 68°F (20°C)
Burst Pressure	Refer to burst pressure characteristic chart
Operating Temperature	Air: -4° to 176°F (-20° to 80°C) Water: 40° to 176°F (5° to 80°C)
Material	Polyolefin
Hardness	Shore D 54

В

Bag

Bag

How To Order

TPS Soft

Polyolefin Metric

Syn

100m

tric Size		Color Indication				
Symbol Tube Size		Symbol	Color			
0425	4mm	В	Black			
0604	6mm	W	White			
0805	8mm	R	Red			
1065	10mm	BU	Blue			
1208	12mm	Y	Yellow			
		G	Green			

0604

ength Per F	Roll
Symbol	Roll Size
20	20m

Longer lengths available
upon request

100m

100

Bag

Packaging Design **Metric Size Tubing** Length 10mm 12mm 4mm 6mm 8mm 20m Bag Bag Bag Bag Bag

Bag

Bag

17

Series TPS

Polyolefin Tubing

Antistatic Tubing

ductive Dimensions

Flame resistant conductive tubing to minimize problems associated with static electricity



Burst Pressure Characteristics Chart



⚠ Caution

- 1. Contact SMC regarding other fluids.
- **2.** When using tubing with SMC fittings, the chemical resistance of the fitting has to be investigated as well.

Metric	Series TAS					
Model	TAS3222	TAS0425	TAS0604	TAS0805	TAS1065	TAS1208
Tube OD (mm)	3.2	4	6	8	10	12
Tube ID (mm)	2.2	2.5	4	5	6.5	8
Min. bending radius (mm)	12	12	15	19	27	32

Specifications

Operating Fluid	Air
Max. Operating Pressure	174 psi (1.2MPa) at 68°F (20°C)
Burst Pressure	Refer to burst pressure characteristic chart
Operating Temperature	32° to 104°F (0° to 40°C)
Material	Conductive Nylon + Fire resistant Nylon (UL-standard, V-O)
Surface Resistance	10 ⁴ to 10 ⁷ Ohms
Hardness	Shore D 48



			Metric	Size	Tubing
3.2mm	4mm	6mm	8mm	10mm	12mm
Bag	Bag	Bag	Bag	Bag	Bag
Reel	Reel	Reel	Reel	Reel	Reel
	Bag	Bag Bag	3.2mm4mm6mmBagBagBag	3.2mm4mm6mm8mmBagBagBagBag	3.2mm4mm6mm8mm10mmBagBagBagBagBag

Series TAU

Antistatic Tubing

Conductive tubing minimizes problems associated with static electricity



Dimensions

Metric	Series TAU					
Model	TAU3220	TAU0425	TAU0604	TAU0805	TAU1065	TAU1208
Tube OD (mm)	3.2	4	6	8	10	12
Tube ID (mm)	2	2.5	4	5	6.5	8
Min. bending radius (mm)	10	10	15	20	27	35

Specifications

Operating Fluid	Air
Max. Operating Pressure	130 psi (0.9MPa) at 68°F (20°C)
Burst Pressure	Refer to burst pressure characteristic chart
Operating Temperature	32° to 104°F (0° to 40°C)
Material	Conductive polyurethane
Surface Resistance	10 ⁴ to 10 ⁷ Ohms
Hardness	Shore A 95



Packaging Design				Metric	Size	Tubing
Length	3.2mm	4mm	6mm	8mm	10mm	12mm
20m	Bag	Bag	Bag	Bag	Bag	Bag
100m	Reel	Reel	Reel	Reel	Reel	Reel

Burst Pressure Characteristics Chart



\triangle Caution

- 1. Contact SMC regarding other fluids.
- **2.** When using tubing with SMC fittings, the chemical resistance of the fitting has to be investigated as well.

FR Soft Nylon Tubing

Flame resistant tubing for use in spot welding environments



Burst Pressure Characteristics Chart



Dimensions

Inch Series TIRS Model TIRS07 TIRS11 TIRS13 Tube OD (Inches) 1/4 5/16 3/8 1/2 Tube ID (Inches) 0.167 0.2 0.25 0.35 Min. bending radius (Inches) 0.91 0.75 1.38 1.06

*When ordering 5/16 tubing, please refer to 8mm tubing.

Metric **Series TRS** Model TRS0603 TRS0805 TRS1065 TRS1208 Tube OD (mm) 10 12 6 8 Tube ID (mm) 5 6.5 8 3 Min. bending radius (mm) 17 19 27 32

Specifications

-	
Operating Fluid	Air, Water
Max. Operating Pressure	175 psi (1.2MPa) at 68°F (20°C)
Burst Pressure	Refer to burst pressure characteristic chart
Operating Temperature	Air: -4° to 140°F (-20° to 60°C)
	Water: 40° to 140°F (5° to 60°C)
Material	Flame resistant Nylon (UL standard V-O)
Hardness	Shore D 48



Note* - For 5/16 size tubing, please refer to 8mm "How to Order" information

G

Color Black White Red

Blue

Green

	TRS	<u>1065</u>	W	
Flame	Metric Size	<u> </u>	Color Indica	tion
Contrayion	Symbol	Tube Size	Symbol	Col
	0603	6mm	В	Bla
	0805	8mm	W	Whi
	1065	10mm	R	Re
	1208	12mm	BU	Blu

<u>100</u>	
Length Per I	Roll
Symbol	Roll Size
20	20m
100	100m

Longer lengths available upon request

\land Caution

- 1. Can be used with general industrial water. For other fluids please consult SMC.
- 2. Max. operating pressure and minimum bending radius are measured at 68°F.
- 3. When using tubing with SMC fittings, the chemical resistance of the fitting has to be investigated as well.

Packaging Design	Inch Size	e Tubing	
Length	1/4	3/8	1/2
20m	Bag	Bag	Box
100m	Reel	Reel	Reel

Packaging Design		Metric	Size	Tubing
Length	6mm	8mm	10mm	12mm
20m	Bag	Bag	Bag	Bag
100m	Reel	Reel	Reel	Reel

Series TRB

FR Double Layer Tubing

Nylon

Weld splatter resistant double layer tubing uses flame resistant resin for outer layer



Burst Pressure Characteristics Chart



Â Caution

- 1. Can be used with general industrial water. For other fluids please consult SMC.
- **2.** Max. operating pressure and minimum bending radius are measured at 68°F.
- 3. When using tubing with SMC fittings, the chemical resistance of the fitting has to be investigated as well.

Dimensions

Metric	Series '	ſRB		
Model	TRB0604	TRB0806	TRB1075	TRB1209
Inner Tube OD (mm)	6	8	10	12
Inner Tube ID (mm)	4	6	7.5	9
Outer Layer Thickness (mm)	1	1	1	1
Min. bending radius (mm)	15	28	35	45

Specifications

-	
Operating Fluid	Air, Water
Max. Operating Pressure	145 psi (1MPa) at 68°F (20°C)
Burst Pressure	Refer to burst pressure characteristic chart
Operating Temperature	Air: -4° to 140°F (-20° to 60°C)
	Water: 40° to 140°F (5° to 60°C)
Material Inner Tube	Nylon 11
Material Outer Layer	PVC (Equivalent to UL-94, standard V-O)
Hardness Inner Tube	Shore D 53

How To Order

Double Layer

Nylon



20	
	_
_ength Per Roll	l

Symbol	Roll Size
20	20m
100	100m

Longer lengths available upon request

Packaging Design		Metric	Size	Tubing
Length	6mm	8mm	10mm	12mm
20m	Bag	Bag	Bag	Bag
100m	Reel	Reel	Reel	Reel
	<u> </u>		<u> </u>	U



FR Double Layer Tubing

Polyurethane

Weld splatter resistant double layer tubing uses flame resistant resin for outer layer



Burst Pressure Characteristics Chart



▲ Caution

- 1. Can be used with general industrial water. For other fluids please consult SMC.
- 2. Max. operating pressure and minimum bending radius are measured at 68°F.
- **3.** When using tubing with SMC fittings, the chemical resistance of the fitting has to be investigated as well.

Dimensions

Metric	Series TRBU			
Model	TRBU0604	TRBU0805	TRBU1065	TRBU1208
Inner Tube OD (mm)	6	8	10	12
Inner Tube ID (mm)	4	5	6.5	8
Outer Layer Thickness (mm)	1	1	1	1
Min. bending radius (mm)	15	20	27	35

Specifications

•	
Operating Fluid	Air, Water
Max. Operating Pressure	115 psi (0.8MPa) at 68°F (20°C)
Burst Pressure	Refer to burst pressure characteristic chart
Operating Temperature	Air: -4° to 140°F (-20° to 60°C)
	Water: 32° to 105°F (0° to 40°C)
Material Inner Tube	Polyurethane
Material Outer Layer	PVC (Equivalent to UL-94, standard V-O)
Hardness Inner Tube	Shore A 95

1065

How To Order

Flame Resistant Double Layer Polyurethane

Tube
Tube Size
6mm
8mm
10mm
12mm

Color Indication		
Symbol	Color	
В	Black	
W	White	
R	Red	
BU	Blue	
Y	Yellow	
G	Green	

W

1	00	
		_
l er	nath Per Roll	l

Symbol	Roll Size		
20	20m		
100	100m		

Longer lengths available upon request

Packaging Design	Metric	Size	Tubing	
Length	6mm	8mm	10mm	12mm
20m	Bag	Bag	Bag	Bag
100m	Reel	Reel	Reel	Reel



When using TRB/TRBU tubing with SMC One-Touch™ fittings

SMC One-Touch™ fittings are not designed to seal on the outer layer. To make a leak free tubing to fitting connection, one has to remove the outer layer. The fitting will seal on the inner tube. The TRB/TRBU tubing is called out by the diameter of the inner tubing so selection of the correct size fitting will not be a problem.

Example:

TRBU 1208 W — 100 - Nominal diameter is 12mm and overall outside diameter is 14mm when outer layer is included. Requires a 12mm One-Touch® fitting.

Instructions

Locate the cut markings on the tubing. The cut markings are represented by simple dashes. The length of a dash as well as the distance between dashes represent the correct stripping length.

- **1.** Cut the tubing on one of the cut markings. Cut through both inner tubing as well as outer layer.
- 2. Strip off outer layer using the cut markings as guidance.
- 3. Install tubing in One-Touch[™] fitting



Strip off external layer only

To simplify cutting and stripping of the tubing, SMC offers the TKS line of stripping tools.





Series TM Multiple Tubing Holder

Can be separated at any position depending on the number of tubes. Manufactured from flame resistant resin (Equivalent to UL-94 Standards V-0).

Applicable Tubing O.D.	Model	Number	of tubing	g (MAX.)					
Tubing O.D.	INIOUEI	6	8	12	Size: Nominal size X length	Number of pieces			
4	TM-04				2 X 6				
6	TM-06				2.6 X 8				
8	TM-08				2.0 × 8	4			
10	TM-10				3 X 8				
12	TM-12				3×0				

How To Use

\land Caution

1. The multiple tubing holder can be cut apart according to the number of tubes to be connected.

CUTTING METHOD Align the cutter with the cutting groove and cut the holder.



- **2.** Cut the multiple tubing holder at a desired position and mount it on the equipment with the attached phillips countersunk tapping screws.
- **3.** Align the tube with the holding position and push down to fit into the holding part.

Size Change

on the back side.

Push both sides at once to release.

Push

Indication of size

Reversed and fixed at the same position as before. Applicable tube size is indicated

Reverse

4. Pull tubing up to remove it from the holder.

Series TG Tube Releasing



Part No.	Applicab	le Tube Size	Applicable Tube Material	Color	Weight
TG-1	Metric size	ø4, ø6	Nylon, Soft Nylon	ylon Blue	
TG-2	Inch size	ø1/8", ø1/4"	Polyurethane	Red	33g

- ▲ Aids in the connection and removal of tubing in applications where One-touch[™] fittings are located close together, such as on a valve manifold.
- Easy one handed operation.
- Available for two sizes of applicable tubes. Easy exchange with one touch.

How To Use

\land Caution

Process

Put the end of tool into the release bushing parallel to the tube.



After inserting, grasp the handle tightly and insert the end of the tube to the stroke end.

Note) Insert firmly to guard against accidental tube release.



After inserting end of tube, relax your grip on the tool. Returning force of spring releases the tube.

Series TK, TKS, TB-3VS

Tubing Cutters

TK-1

Applicable tubing O.D.: 13mm or less.

TK-2 Applicable tubing O.D.: 18mm or less.

TK-3 (Simple type)

Applicable tubing O.D.: 12mm or less.







Double Layer Tubing Stripper Series TKS

Allows the outer layer of SMC's double layer tubing to be stripped off easily.



Variations

Model	Tip Color	Applicable Tubing*
TKS-06	Orange	TRB0604,TRBU0604
TKS-08	Yellow	TRB0806, TRBU0805
TKS-10	Blue	TRB1075, TRBU1065
TKS-12	Green	TRB1209, TRBU1208

* Inner tubing material / TRB: soft nylon, TRBU: Polyurethane

Vertical Tubing Stand Series TB-3VS



Dimensions: 37-1/4" w x 27-9/16" d x 68-11/16" h

Designed for high capacity and reel size flexibility. This stand comes with two cross bars. A third cross bar can be ordered separately (TB-3CB).

This chart does not apply to soft Nylon tubing

This chemical resistance chart is meant to be used as a guideline only.

Due to variables such as temperature and chemical mixture, it is essential to test under actual conditions.

			st
Category	Concentration		erature
Inergenie Dese	%	23°C	60°C
Inorganic Base Caustic soda	50	•	^
Caustic potash	50	•	Δ
Aqueous ammonia	High	•	•
Ammonia Inorganic Acid		•	•
Chromic acid	10	Х	Х
Hydrochloric acid	1	\triangle	X
Hydrochloric acid	10	Х	Х
Nitric acid	10 50	X O	X
Phosphoric acid Sulfuric acid	50	0	$\hat{\Delta}$
Sulfuric acid	10	Õ	X
Sulfuric anhidride		\triangle	Х
Inorganic Base	Deete	•	•
Aluminum sulfate Ammonium sulfate	Paste Paste		~
Barrium chloride	Paste	ě	•
Calcium arsenate	Paste	•	•
Calcium chloride	Paste Paste	•	•
Copper sulfate Ammonium phosphat			Δ
Magnesium chloride	50	ě	•
Potassium nitrate	Paste	0	Х
Potassium sulfate	Paste	•	•
Sodium carbonate Sodium chloride	Paste Saturated	•	
Sodium sulfate	Paste		Δ
Sodium phosphate	Paste	•	•
Zinc chloride	Saturated		\triangle
Inorganic Compound Agricultural chemical			-
Bromide		X	-
Chlorine		X	Х
Carbon		Х	Х
Hydrogen		•	•
Hydrogen peroxide Bleaching agent	20		- X
(Chlorus acid solution))		~
Mercury	/	•	•
Oxygen		•	\triangle
Ozone Potassium permanga	na 5	∆ X	X
Sea water	na J	ê	•
Sulfur		•	-
Water		•	•
Carbonate water Organic Base		•	-
Aniline	Pure	\triangle	Х
Diethanolamie	20	•	0
Pyridine	Pure	\triangle	Х
Urea Organic Acid		•	Δ
Acetic acid	50	Х	Х
Acetic acid anhydride		Δ	X
Citric acid	Saturated	•	\triangle
Formic acid Lactic acid	98	X	×
Oleic acid			
Oxalic acid		ě	Δ
Pircric acid		\triangle	Х
Stearic acid	Saturated	•	
Tartaric acid Uric acid		•	
Hydrocarbon Group		•	•
Acetylene		•	•
Benzene	100	•	Δ
Butane Cyclohexane	100	•	×
Decaline	100	ĕ	è
Freon 12		•	-
Freon 22		•	-
Methane		•	•
Naphthalene Propane			
Styrene		•	-
Toluene	100	•	\triangle
Xylene	100	*	\triangle
Benzyl alcohol Butyl alcohol		∆ 0	X X
Ethyl alcohol	Pure	0	$\hat{\Delta}$
Glycerin	Pure	X	

		т	est
Category	Concentration	Temp	erature
	%	23°C	60°C
Alcohol Group - con't			
Glycol		Х	0
	Pure	0	Δ
Aldehyde Ketone		•	X
Acetaldehyde	Pure	0	X
Acetone Benzealdehyde	100	X	∆ X
Formalin	Industrial Use	ê	X
Methylethyl ketone	100	0	Δ
Methylisobutyl Ketone		Х	Δ
Chloride Solvent Group			
Carbontetrachloride	100	X	Х
Methylbromide	400	• V	-
Methylchloride Perchloroethylene	100	X	-
Trichloroethane		Δ	-
Trichloroethylene	100	\wedge	Х
Phenol Group			
· ·	Saturated	Х	Х
Organic Base, Ether / E	ster Group		
Amylacetate	100	•	
Butylacetate	100		
Dioctylphosphate Dioctylphthalate			
Ethylacetate	100		Ŏ
Fatty acid ester	100	•	Ŭ
Methylacetate		٠	•
Methylsulfate		•	-
Sulfuric ether		•	
Tributyl phosphate		•	•
Tribledyl phosphate Other Organic Compour	hn	-	•
Anethole	iu	•	
Carbon disulfide		Õ	Х
Diacetone alcohol		•	\triangle
Ethylene oxide		•	Δ
Furfural		•	Δ
Glucose		•	0
Glucose chloride Tetraethyl lead		×	
Other			-
City gas		•	-
Oil		•	-
Grease		•	-
Regular gasoline		•	0
High-octane gasoline		•	0
Diesel Oil			0
Naphtha solvent Kerosene			0
Crude oil			ě
Styrene		ě	-
Seasoning		•	-
2, 4-D solvent		٠	-
Linderene-DDT		•	-
Oxyquinoline		•	-
Soapy water		•	0
Turpentine oil Edible vinegar		×	-
Thinner		^	
Freon 23 (Subject to	condition)	•	
Grease (Tubing could			

This chemical resistance chart is meant to be used as a guideline only.

Due to variables such as temperature and chemical mixture, it is essential to test under actual conditions.

		Te	est
Category	Concentration	Tempe	erature
	%	23°C	60°C
Inorganic Base			
Caustic soda Caustic soda	10 50	0 	
Aqueous ammonia	100	ō	Δ
Inorganic Acid	10		X
Hydrochloric acid Hydrochloric acid	10 High	∆ X	X
Nitric acid	50	X	
Phosphoric acid	85	X	Х
Sulfuric acid Sulfuric acid	10 50	∆ X	X -
Inorganic Compound			
Hydrogen sulfide Chlorine	Low 100	O X	Δ
Sulfur dioxide	Low	ô	- △
Hydrogen peroxide	30	Δ	Х
Carbon disulfide	100 100	0	∆ 0
Sulfur Water	100	0	0
Organic Base			
Aniline	100 100	\triangle	
Pyridine Urea	Saturated	0	-
Organic Acid			
Acetic acid Citric acid	50 Saturated	∆ 0	\triangle
Formic acid	98	Δ	X
Oleic acid	00	0	\triangle
Nucleic acid		0	\triangle
Tannic acid Glacial acid	100	Δ	∆ X
Alcohol Group			
Cyclohexanol	100	0	∆ O
Butyl alcohol Ethyl alcohol	100 100	0 	Δ
Glycerin	100	0	\triangle
2-ethylhexanol	100	0	\triangle
Methyl alcohol Ethylene glycol	100 50	 ○	 ○
Ethylene glycol	100	Ó	Δ
Cresol	100	\triangle	-
Aldehyde Ketone Acetone	40	\triangle	Δ
Formaldehyde	100	\triangle	-
Benzaldehyde	100	Х	-
Dimethylformaldehyde Methylethylketone	100 100	X X	X X
Chloride Solvent		~	X
Carbon tetrachloride	100	\triangle	-
Ethylenechloride Methylenechloride	100 100	X X	-
Chloroform	100	Δ	Х
Trichloroethylene	100	Δ	Х
Phenol Group Phenolnitro	Saturated	0	Δ
Nitrobenzene	100	Δ	-
Ester/Ether Group	400	0	
Ethylether Butyl acetate	100 100	O X	∆ X
Dioctyl phthalate		\triangle	-
Ethylacetate	100	X	X
Petroleumether Dibutylphthalate	100	0 	Δ-
Tricledylphosphate		\triangle	-
1.4-dioxin	100	0	\triangle
Tetrahydrofuran Hydrocarbon Group	100	Х	Х
Benzene	100	\triangle	Х
Butane	100	0	\triangle
Hexane Isoctane	100 100	0	\triangle
Cyclohexane	100	\triangle	Х
Toluene	100	X	X
Xylene Freon 12	100	∆ 0	
Thinner		x	Х

Category	Concentration		est erature
	%	23°C	60°C
Oil Group			
Brake oil	Saturated	0	0
ASTM oil	100	0	0
ASTM fuel	100	0	 O
Machine oil	100	0	
Gasoline	100	0	\triangle
Diesel oil	100	0	0
Petroleum oil		0	\triangle
Kerosene		0	
Vegetable oil		0	0
Turpentine oil			Δ
JIS No. 1 oil (100°C)			0
JIS No. 3 oil (100°C)			\triangle
Food Group			
Beer		0	-
Brandy		0	-
Rum		0	0
Juice		0	0
Butter		0	0
Margarine		0	0
Jelly		0	0
Salad oil		0	0
Sausage		0	0
Sugar		0	0
Tea		0	0
Other		_	
Aqueous alum	100	0	0
Synthetic detergent		0	0
Lanolin		0	0
Paraffin		•	0
Ink		0	\triangle
Liquid developer		0	Δ
Sea water		0	0

(Note) ullet: No change; \bigcirc : Resistance for practical use; \triangle : Gradually deteriorated; X: Deteriorated (21 days immersion)

This chemical resistance chart is meant to be used as a guideline only.

Due to variables such as temperature and chemical mixture, it is essential to test under actual conditions.

Category	Concentration		est erature
	%	20°C	60°C
Acetaldehyde*	100	Δ	Х
Acetone*	100	\triangle	Х
Aniline	100	\triangle	Х
Amyl alcohol* Ammonia water	100 0.88 spar liquid	0	X
Ammonia	0.88 spgr liquid Dry gas	0	ő
Sodium aluminate		õ	Õ
Linseed oil*	100	\triangle	Х
Sodium benzoate Sodium nitrite	Saturation	0	0
Sodium nitrite	_	0	0
Carbon monoxide	_	ŏ	ŏ
Sulfur		0	\triangle
Yeast		0	0
Ethyl alcohol	<96 100	0 Δ	Δ
Ether	100	X	
Ethylene glycol	—	Δ	\triangle
Chlorine	Dry gas	\triangle	Х
Onionne	Liquid 100%	X	X
Chlorine water	2% Saturation	0	0
Calcium chlorate	Saturation	0	0
Potassium chlorate	Saturation	õ	ŏ
Hydrochloric acid	10	0	Х
Aniline chloride	_	Х	
Aluminum chloride		0	\triangle
Zinc chloride Barium chloride	Saturation Saturation	0	0
Calcium chloride		0	ő
Copper chloride	_	Õ	Õ
Iron chloride	Saturation	0	0
Magnesium chloride	Saturation	0	0
Mercury chloride Nickel chloride	Saturation	0	0
Potassium chloride	Saturation Saturation	0	0
Sodium chloride	Saturation	ŏ	õ
Tin chloride	Saturation	0	Ō
Ammonium chloride	Saturation	0	0
Methyl chloride		X X	Х
Phosphorus oxychlor Diethyl ether*		x	<u>×</u>
Ammonium persulfate	ə —	0	0
Potassium persulfate	—	0	0
Potassium permanga	nate —	0	0
Sodium peroxide Hydrogen peroxide	-	0	0
Sea water	_	0	ő
	80 or less	Õ	Ō
Formic acid	100	\triangle	\triangle
Xylene*	100	X	Х
Metallic soap* Beef tallow	-	0	_
Milk	_	0	0
Chloroform*	100	Δ	X
Chlorosulfonic acid	_	Х	Х
Chromic acid	Electrolyte	0	0
Potassium chromate Chrome alum	Saturation	0	0
Citric acid	Saturation	0	0
Creosote*	_	X	_
Cresol*	_	Х	—
Cresylic acid	50	0	0
Glycerol	—	0	Δ
D-glucose Silicofluoric acid	_	0	0
Antimony pentachlori	de —	0	0
Phosphorus pentoxid	e 100	0	0
Mineral oil*	—	Δ	Х
Soda Solicylic coid	_	0	0
Salicylic acid		0	0
Acetic acid	10~50	õ	Δ
	60 or less	\triangle	Х
Amyl acetate*	_	Х	_
Ethyl acetate	_	\triangle	X
Methyl acetate Sodium acetate		X	X
Lead acetate	Saturation	0	0
Phosphorus trichlorid		0	
Antimony trichloride	_	0	0
Boron trifluoride		0	_

Category	Concentration		est erature			
Category						
Owngon	% 100	20°C	60°C X			
Oxygen Zinc oxide		0	Ô			
Cychlohexanol	—	\triangle	Δ			
Cyclohexanone Copper cyanide	_	X	0			
Silver cyanide	_	õ	0			
Potassium cyanide	Saturation	0	0			
Sodium cyanide Mercury cyanide	Saturation Saturation	0	0			
	5~25	0	Δ			
Nitric acid	50 70~98	∆ X	X X			
Ammonium nitrate	Saturation	ô	Ô			
Calcium nitrate	Condensation	0	0			
Copper nitrate Potassium nitrate		0	0			
Silver nitrate		0	0			
Stronium nitrate		0	Ó			
Magnesium nitrate	Saturation	0	0			
Nickel nitrate Salt water (Brine)	Condensation	0	0			
Cane sugar	_	0	0			
Oxalic acid	Saturation	0	0			
Tartaric acid	10 Saturation	0	0 4			
Vegetable oil*	_	\triangle	Х			
Bromine	Dry gas	X	X			
Hydrobromic acid	50 100	0	0			
Methyl bromide		Х	Х			
Potassium bromide	Saturation	0	0			
Potassium bromate Ammonium bicarbona		0	0			
Sodium bicarbonate	Saturation	ŏ	Ö			
Potassium bicarbonate		0	0			
Sodium hydrogen sulfa Potassium hydrogen su		0	0			
Sodium bisulfate	Saturation	õ	Ö			
Potassium bisulfate	—	0	0			
Potassium dichromate Sodium hypochlorite	e Saturation 15	0	0			
Calcium hypochlorite	15	õ	0			
Sodium hyposulfite	—	0	0			
Tetraethyl lead Carbon tetrachloride	100	O X				
Camphor oil*	_	Х	X			
Silicon fluid*	—	\triangle	Х			
Developer Emulsifier	_	0	0			
Hydrogen	100	õ	0			
Aluminum hydroxide	—	0	0			
Barium hydroxide Calcium hydroxide	Saturation	0	0			
,		0	0			
Potassium hydroxide	Condensation*	0	0			
Sodium hydroxide	<40 Condensation*	0	0			
Magnesium hydroxide	Condensation*		0			
Ammonium hydroxide		0	0			
Mercury Stearie acid		0	0			
Stearic acid Cetyl alcohol*	100	0				
Soapy water	_	0	0			
Petroleum ether	_	X	X			
Petroleum Tannic acid	10	X O	X O			
Ammonium carbonate		0	0			
Barium carbonate	Saturation	0	0			
Calcium carbonate Magnesium carbonate	e Saturation	0	0			
Sodium carbonate	Condensation	0	0			
Potassium carbonate		0	0			
Ammonium thiocyanate Potassium thiosulfate		0	0			
Sodium thiosulfate	Saturation	0	0			
Starch	Saturation	0	0			
Turpentine oil* Dextrose	100 Saturation	X O	X			
Trichloroethylene*	100	x	x			
Triethanolamine*	100	0	Х			
Animal oil* Soft soap*	_	∆ 0	X O			
con soup	_	J	J			

Cotomorr			est
Category	Concentration	Temp	erature
	%	20°C	60°C
Nitrobenzene*	—	Δ	Х
Diethyl ether*	_	\triangle	Δ
Carbon dioxide Carbon disulfide	100 100	O X	O X
Ethylene dichloride*	100	X	x
	Dry gas	0	Õ
Sulfur dioxide	Humid gas	0	\triangle
Potassium dichromate	•	0	0
Emulsifier Lactic acid	-	0	0
Paraffin	_	Δ	X
Hydroquinone		0	0
Beer		0	Ó
Castor oil*		Х	_
Arsenic acid	100	0	0
Lead arsenate	1	0	0
Picric acid	Alcohol 10%	ŏ	ŏ
Surface active agent*	_	0	Ó
Butyl alcohol*	100	0	Х
Dioctyl phtalate*		\triangle	X
Dibutyl phthalate* Phenol*	100	∆ X	
Sodium ferricyanide	 Saturation	0	0
Sodium ferrocyanide	Saturation	0	0
Grape sugar (Glucose		0	Ō
Fluorine		\triangle	Х
Aluminum fluoride	_	0	0
Copper fluoride		0	0
Potassium fluoride Sodium fluoride	Saturation	0	0
	<60	0	0
Hydrofluoric acid	75	õ	Ā
Benzaldehyde*	_	Х	_
Benzene*	_	Х	Х
Benzenesulfonic acid	_	X	—
Benzyl alcohol Boric acid	_	X	0
Sodium borate	_	0	0
Potassium borate	_	õ	Ő
Formaldehyde	40	0	0
Water		0	0
Methyl alcohol	<50	0	0
Methyl ethyl ketone*	100 100		∆ X
Ammonium metaphosphat		0	Ô
Sodium metaphosphate		Õ	õ
Alum		Ó	0
Monochloroacetic benze		X	X
	10~60	0	
Sulfuric acid	70 80	O A	X X
	80 98	X	x
Aluminum sulfate	_	0	0
Barium sulfate	Saturation	Ó	0
Calcium sulfate	—	0	0
Copper sulfate	Saturation	0	0
Iron sulfate Magnesium sulfate		0	0
Manganese sulfate		0	0
Nickel sulfate	Saturation	0	0
Potassium sulfate	Condensation	0	0
Sodium sulfate	Saturation	0	0
Zinc sulfate Ammonium sulfate	Saturation Saturation	0	0
Aniline sulfate		x	X
Barium sulfide	Saturation	0	0
Potassium sulfide	Condensation	0	0
Sodium sulfide	25	0	0
	Saturation	0	0
Hydrogen sulfide		0	_
Ammonium sulfide	Saturation <90	0	O X
	95	Δ	X
Phosphoric acid		0	Ô
	—	0	
Phosphoric acid Calcium phosphate Potassium phosphate	_	0	0
Calcium phosphate Potassium phosphate Sodium phosphate		0	0
Calcium phosphate Potassium phosphate		0	0

 $(\textit{Note}) \bigcirc: \textit{Resistant}; \triangle: \textit{Slightly deteriorated or absorbed}; X: \textit{Non-resistant}, *: \textit{Possibility of stress cracks}$

Safety Instructions

These safety instructions are intended to prevent a hazardous situation and/or equipment damage. These instructions indicate the level of potential hazard by a label of "**Caution**", "**Warning**" or "**Danger**". To ensure safety, be sure to observe ISO 4414^{Note 1}, JIS B 8370^{Note2} and other safety practices.



- Note 1) ISO 4414: Pneumatic fluid power Recommendations for the application of equipment to transmission and control systems.
- Note 2) JIS B 8370: General Rules for Pneumatic Systems.



1. The compatibility of pneumatic equipment is the responsibility of the person who designs the pneumatic system or decides its specifications.

Since the products specified here are used in various operating conditions, their compatibility for the specific pneumatic system must be based on specifications or after analysis and/or tests to meet your specific requirements.

- 2. Only trained personnel should operate pneumatically operated machinery and equipment. Compressed air can be dangerous if an operator is unfamiliar with it. Assembly, handling or repair of pneumatic systems should be performed by trained and experienced operators.
- 3. Do not service machinery/equipment or attempt to remove components until safety is confirmed.
 - 1. Inspection and maintenance of machinery/equipment should only be performed after confirmation of safe locked-out control positions.
 - 2. When equipment is to be removed, confirm the safety process as mentioned above. Cut the supply pressure for this equipment and exhaust all residual compressed air in the system.
 - 3. Before machinery/equipment is re-started, take measures to prevent shooting-out of the cylinder piston rod etc. (Bleed air into the system gradually to create back-pressure.)
- 4. Contact SMC if the product is to be used in any of the following conditions:
 - 1. Conditions and environments beyond the given specifications, or if product is used outdoors.
 - 2. Installation on equipment in conjunction with atomic energy, railway, air navigation, vehicles, medical equipment, food and beverages, recreation equipment, emergency stop circuits, press applications, or safety equipment.
 - 3. An application which has the possibility of having negative effects on people, property, or animals, requiring special safety analysis.

Tubing Precautions

Selection

\land Warning

1. Confirm the specifications

The products appearing in this catalog are designed for use only in compressed air systems (Including vacuum).

Do not use outside the specified ranges of pressure, temperature, etc., as this may cause damage or malfunction (Refer to specifications).

\land Caution

1. Use tubing at or above the minimum bend radius. Using below the minimum bend radius can cause breakage or kinking of the tube.

Mounting

\land Caution

- **1.** Before mounting confirm the model and size, etc. Also confirm that there are no blemishes, nicks or cracks in the product.
- 2. When connecting tubing, consider factors such as changes in the tubing length due to pressure and allow sufficient leeway.
- **3.** Mount so that fittings and tubing are not subjected to twisting, pulling or moment loads. This can cause damage to fittings and kinking, bursting or disconnection of tubing, etc.
- **4.** Mount so that tubing is not damaged due to tangling or abrasion. This can cause kinking, bursting or disconnection of tubing, etc.

Applications

🖄 Warning

1. Refer to chemical resistance charts

Operating Environment

\land Warning

- 1. Do not use ordinary fittings and tubing in locations where static electric charge will cause a problem. This can cause defects or failure of the system, etc. In this kind of location, the use of antistatic fittings (Series KA) and antistatic tubing (Series TA) is recommended.
- **2.** Do not use ordinary One-touch fittings in locations where spatter is generated. There is a danger of spatter causing a fire. In this kind of location, the use of flame resistant fittings (Series KR, KRM) and flame resistant tubing (Series TRS, TRB, TRBU) is recommended.

Maintenance

\land Caution

1. Make periodic inspections to check for the following problems, and replace parts as necessary

- A) Blemishes, nicks, abrasions, corrosion
- B) Air leakage
- C) Twisting, kinking or tangling of the tubing
- D) Hardening, deterioration or softening of the tubing

Packaging Options

SMC tubing is sold in 3 basic packages:

Bag Dispenser Box Reel

The quantity, diameter and type of the tubing ordered defines the type of package used. The standard package option is indicated in the catalog on the appropriate product page.

SMC recognizes the need for alternative packaging options. Please contact a SMC representative for help with your request.

Tubing Length Other Than Indicated In Catalog

Please contact a SMC representative for information regarding this request. SMC will strive to meet your requirements.

Splicing Policy

SMC does not splice tubing.

Custom Marking on Tubing

Please contact a SMC representative for information regarding this request.

Hardness Comparison for Thermoplastics

<mark>Shore A</mark> Shore D Rockwell R	20	30	40	50	60	70	80	100 50	60		90	100	110	120	130	140	150
Flexible								 		 	 						Rigid

Color Chart for Polyurethane Tubing

Symbo	l Color		Symbol	Color	
В	Black		G4	Dark Green	
BU	Blue		GR1	Gray (solid)	
С	Clear		GR2	Lt. Gray (solid)	
G	Green		P1	Neon Pink	
R	Red		PU1	Purple (solid)	
w	White		PU2	TR Purple	
Y	Yellow		R1	Red (solid)	
YR	Orange		R2	TR Red	
BU1	Blue (solid)		S1	Silver	
BU2	TR Blue		Y1	Yellow (solid)	-
BU3	Med. Blue		Y2	TR Yellow	
BR1	Brown (solid)		Y3	Neon Yellow	
G1	Green (solid)		YR1	TR Orange	
G2	TR Green		YR2	Neon Orange	11220
G3	Neon Green				
	Note: Ouisle	hin colore in	aluda, Dia	ok Plue Clear	

Note: Quick ship colors include: Black, Blue, Clear, Green, Red, White, Yellow and Orange.





Contact your Sales Representative about SMC's Fitting Cabinet Program

