

Supporting Information

Orientation control of two-dimensional perovskites by incorporating carboxylic acid moieties

Ryosuke ARAI^a, Masahiro YOSHIKAWA-FUJITA^a, Yuko TAKEOKA^{a} and Masahiro
RIKUKAWA^a*

^a Faculty of Science and Engineering, Sophia University, 7-1 Kioi-cho, Chiyoda-ku, Tokyo, 102-8554, Japan.

Elemental analysis data of compounds

Elemental analysis data for $[\text{HOOC}(\text{CH}_2)_{n-1}\text{NH}_3\text{I}]_2\text{PbI}_4$ ($n = 3$), $\text{C}_6\text{H}_{16}\text{N}_2\text{PbI}_6$; Calc. C 8.05, H 1.80, N 3.13, I 56.72%, Exp. C 8.40, H 1.69, N 3.20, I 54.70%.

Elemental analysis data for $[\text{HOOC}(\text{CH}_2)_{n-1}\text{NH}_3\text{I}]_2\text{PbI}_4$ ($n = 4$), $\text{C}_8\text{H}_{20}\text{N}_2\text{PbI}_6$; Calc. C 10.41, H 2.18, N 3.03, I 54.99%, Exp. C 10.46, H 1.62, N 2.99, I 55.69%.

Elemental analysis data for $[\text{HOOC}(\text{CH}_2)_{n-1}\text{NH}_3\text{I}]_2\text{PbI}_4$ ($n = 7$), $\text{C}_{14}\text{H}_{32}\text{N}_2\text{PbI}_6$; Calc. C 16.69, H 3.20, N 2.78, I 50.40%, Exp. C 16.52, H 2.80, N 2.69, I 50.79%.

Elemental analysis data for $[\text{CH}_3(\text{CH}_2)_{n-1}\text{NH}_3\text{I}]_2\text{PbI}_4$ ($n = 3$), $\text{C}_6\text{H}_{20}\text{N}_2\text{PbI}_6$; Calc. C 8.63, H 2.41, N 3.35, I 60.79%, Exp. C 7.99, H 1.71, N 3.04, I 59.74%.

Elemental analysis data for $[\text{CH}_3(\text{CH}_2)_{n-1}\text{NH}_3\text{I}]_2\text{PbI}_4$ ($n = 4$), $\text{C}_8\text{H}_{24}\text{N}_2\text{PbI}_6$; Calc. C 11.13, H 2.80, N 3.25, I 58.81%, Exp. C 10.80, H 2.58, N 3.11, I 57.78%.

Elemental analysis data for $[\text{CH}_3(\text{CH}_2)_{n-1}\text{NH}_3\text{I}]_2\text{PbI}_4$ ($n = 7$), $\text{C}_{14}\text{H}_{36}\text{N}_2\text{PbI}_6$; Calc. C 17.75, H 3.83, N 2.96, I 53.59%, Exp. C 17.96, H 3.25, N 3.14, I 52.26%.




Figure S1. D -spacing values of (a) $[\text{HOOC}(\text{CH}_2)_{n-1}\text{NH}_3\text{I}]_2\text{PbI}_4$ and (b) $[\text{CH}_3(\text{CH}_2)_{n-1}\text{NH}_3]_2\text{PbI}_4$ films as a function of carbon atoms in organic amines.




Figure S2. 2D WAXS images of (a) $[\text{HOOC}(\text{CH}_2)_6\text{NH}_3]_2\text{PbI}_4$ and (b) $[\text{CH}_3(\text{CH}_2)_6\text{NH}_3]_2\text{PbI}_4$ ($n = 7$) films.