

Suppl. Table 1. Characteristics of the examined stents

<b>Name</b>	<b>Company</b>	<b>Material</b>	<b>Coating</b>	<b>Nominal diameter (mm)</b>	<b>Length (mm)</b>	<b>Strut thickness (mm)</b>
Multilink Vision	Abbott	Cobalt-chromium alloy	None	3	23	0.081
Apolo Bionert	Iberhospitex	Stainless steel 316L	None	3	14	0.115
Tantal Coronary	Abbott	Tantal	None	3	19	0.58
Coroflex Please	Braun	Stainless steel 316L	Polysulfone + Paclitaxel	3	19	0.12
Chrono	Sorin Biomedica	Cobalt-chromium alloy	Carbofilm	3	20	0.08
PRO Kinetic	Biotronik	Cobalt-chromium alloy	PROBIO, SiC	3	15	0.06
Omega	Boston Scientific	Platinum-chromium alloy	None	3	16	0.081
Liberté	Boston Scientific	Stainless steel 316L	PTFE	3	20	0.096
Radius	Boston	Nitinol	None	3	20	0.08–

	Scientific					0.09
Promus Element Plus	Boston Scientific	Platinum- chromium alloy	Drug/Polymer coating	3	20	0.081