

Printing Carpets Nederland bv
Flevolaan 60 F
1382 JZ WEESP
Nederland



Your notice of
13-02-2017

Your reference

Date
03-04-2017

Analysis Report 17.00886.43

Required tests :

EN 13501-1 (2007) + A1 (2009)

Identification number	Information given by the client	Date of receipt
T1703256	Digital floor vinyl type 1	13-02-2017

Kristina De Temmerman

Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.
The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.
In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.

CENTEXBEL • textile competence centre • www.centexbel.be • www.vkc.be

Inrichting erkend bij toepassing van de besluitwet van 30-01-1947 • Établissement reconnu par application de l'arrêté-loi du 30-01-1947
GENT • Technologiepark 7 • BE-9052 Zwijnaarde, Belgium • phone +32 9 220 41 51 • fax +32 9 220 49 55 • gent@centexbel.be
GRÂCE-HOLLOGNE • Rue du Travail 5 • BE-4460 Grâce-Hollogne, Belgium • phone +32 4 296 82 00 • g-h@centexbel.be
KORTRIJK • Etienne Sabbelaan 49 • BE-8500 Kortrijk, Belgium • phone +32 56 281828 • fax +32 56 281830 • info@vkc.be
VAT BE 0459.218.289 • IBAN BE44 2100 4729 6545 • BIC GEBABEBB

Reference: T1703256 - Digital floor vinyl type 1

Information given by the client

Product standard	EN 13501-1 (2007) + A1 (2009)
Floor covering type	Polyvinyl chloride floor coverings with foam layer
EN product standard	EN 651
FR treated	yes
Mass	1700 g/m ²
Thickness	2.3 mm

Notified body No: 0493

Reference: T1703256 - Digital floor vinyl type 1

Reaction to fire tests – Ignitability of building products subjected to direct impingement of flame - Single-flame source test

Product standard EN 13501-1 (2007) + A1 (2009)

Classification of resilient floor coverings in accordance with EN 14041 (2004) § 4.1.4
 “The resilient floor coverings listed in Table 3, in the end uses identified in the table, are classified without further testing (CWFT) in the classes shown and do not require testing in respect of these end uses and classes”.

Table 3 – Classes of reaction to fire for resilient floor coverings, classified without further testing

Floor covering type ¹	EN product standard	Minimum mass (kg/m ²)	Maximum mass (kg/m ²)	Minimum overall thickness (mm)	Class ² Floorings
Plain and decorative Linoleum	EN 548	2.3	4.9	2	Efl
Homogeneous and heterogeneous polyvinyl chloride floor coverings	EN 649	2,3	3,9	1,5	Efl
Polyvinyl chloride floor coverings with foam layer	EN 651	1.7	5.4	2	Efl
Polyvinyl chloride floor covering with cork-based backing	EN 652	3.4	3.7	3.2	Efl
Expanded (cushioned) polyvinyl chloride floor coverings	EN 653	1,0	2,8	1,1	Efl
Semi-flexible polyvinyl chloride tiles	EN 654	4.2	5.0	2	Efl
Linoleum on corkment backing	EN 687	2.9	5.3	2.5	Efl
Homogeneous and heterogeneous smooth rubber floor coverings with foam backing	EN 1816	3.4	4.3	4	Efl
Homogeneous and heterogeneous smooth rubber floor coverings	EN 1817	3.0	6.0	1.8	Efl
Homogeneous and heterogeneous relief rubber floor coverings	EN 12199	4.6	6.7	2.5	Efl
¹⁾ Floor covering loose laid over any wood based substrate of at least Class D-s2,d0 or any substrate of at least Class A2-s1,d0. ²⁾ Class as provided for in Table 2 in the Annex to Decision 2000/147/EC.					

Classification

Class E_n

Reference: T1703256 - Digital floor vinyl type 1

Reaction to fire tests for floorings - Determination of the burning behaviour using a radiant heat source

Date of ending the test	09-03-2017
Standard used	EN ISO 9239-1 (2010)
Product standard	EN 13501-1 (2007) + A1 (2009)
Deviation from the standard	-
Conditioning	23°C, relative humidity 50% Minimum 14 days or until constant mass is achieved

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test: they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

Test specimen

Substrate	Fibre cement board - density (1800 ± 200) kg/m ³
Mounting	Stuck down with UZIN UZ 57 / Unipro - low emission, solvent-free dispersion adhesive – "EC1 very low emission"
Cleaning	Specimens have not been cleaned

Radiant heat flux

	Flame spread distance (cm)			Flame time	Heat flux *
	10 min	20 min	30 min		
Width					
#1	<11	<11	<11	12 min 00 s	≥ 11
Length					
#1	<11	<11	<11	12 min 00 s	≥ 11
#2	<11	<11	<11	12 min 00 s	≥ 11
#3	<11	<11	<11	12 min 00 s	≥ 11
Average					≥ 11

* Heat flux at the time of flame extinguishment or after a test duration of 30 minutes.

Fire classification in accordance with EN 13501-1 (2007) + A1 (2009)		
Class	EN ISO 11925-2 or CWFT	EN ISO 9239-1 (test duration = 30 min)
B _{fl}	E _{fl}	heat flux ≥ 8,0 kW/m ²
C _{fl}	E _{fl}	heat flux ≥ 4,5 kW/m ²
D _{fl}	E _{fl}	heat flux ≥ 3,0 kW/m ²

Smoke production: Light attenuation

	Maximum (%)	Total (%.min)
Width		
#1	3	22
Length		
#1	2	27
#2	2	18
#3	3	22
Average		22

Additional classification in accordance with EN 13501-1 (2007) + A1 (2009)	
smoke production ≤ 750%.min	s1
smoke production > 750%.min	s2

Reaction to fire classification : B_n/ s1
*Glued on a non-combustible substrate**

** End use substrates of classes A1 or A2-s1,d0 (ISO 13238:2010 § 5.2.2)*

Limitations

This classification document does not represent type approval or certification of the product.