BLAST MEDIA DATA SHEET



GUYSON IRON SILICATE

(for use with portable pressure pots)

GENERAL

Guyson Iron Silicate is often better known by its original name of copper slag. It is a very cost effective, expendable, synthetic mineral abrasive, manufactured from the waste granulated slag produced by copper refineries.

In appearance, the product is glassy and it tends towards brittle fracture upon impact, which produces a great deal of dust. This property means that it is only suited to use in open blasting applications and should not be used in any re-circulating systems. However, if used as intended, the abrasive nature of the product makes it ideal for rapid corrosion removal prior to a re-coating process.

Users should be mindful of the fact that although not harmful to health, the black dust created should be regarded as a nuisance by anyone coming into contact with it.

TYPICAL APPLICATIONS

Mainly site blasting applications e.g. removal of corrosion and paint prior to re-coating. Typical users would be contract blasters working on site, cleaning steelwork, commercial vehicle chassis etc

Chemical Composition (typical)			Physical Data	
Iron Silicate			Shape : Colour :	Angular Black/Glassy
FeO	:	38 – 45%	Specific Gravity:	3.3
SiO ₂	:	33 – 38%	Bulk Density :	1.7 g/cc
Al_2O_3	:	3 – 5%	Hardness :	7 – 8 Mohs
CaO	:	2 – 6%		
MgO	:	1 – 3%	01 4 11.1.1.	Name and Company
Na ₂ O	:	0.5 – 1%	Sizes Available:	Nominal Size Range
MnO	:	0.1 – 0.3%	Coarse :	200 – 1700 (microns)
			Pack Size :	25 kg sack

product once it has been used for blast finishing purposes. However contamination from a specific application or process must also be considered prior to disposal

Iron Silicate is a non-toxic and non-hazardous product. No special disposal precautions are required for the

See Guyson MSDS reference 25 for all other details

Guyson International Limited Snaygill Industrial Estate Keighley Road • SKIPTON • North Yorkshire • BD23 2QR

Tel: +44 (0) 1756 799911 • E-mail: info@guyson.co.uk • Website: www.guyson.co.uk

