



GUYSON TURBOGRIT

for use with turbine wheel and dry compressed air systems

GENERAL

Guyson Turbogrit is heat-treated carbon steel grit, produced by crushing oversized shot pellets. When new, this product is angular but during use, the sharp edges will become round. This allows the blasting process to combine the mass effect of shot with the cutting edge of grit.

Turbogrit would generally be used in wheel/turbine or pressure blast systems, but some of the smaller grits could also be used in suction feed systems.

TYPICAL APPLICATIONS

General engineering, surface treatment and refurbishment applications. Turbogrit is ideal for the removal of corrosion, plating, weld scale etc and the preparation of surfaces prior to painting, bonding etc

Chemical Composition		Sizes Available	:	Nominal Size Range (microns)
Carbon Steel Grit				
Carbon	: 0.85 – 1.20%	G05	:	125 – 300
Manganese	: 0.35 – 1.20%	G07	:	180 – 425
Silicon	: 0.40 – 1.50%	G12	:	300 – 710
Sulphur	: 0.05% maximum	G17	:	420 – 1000
Phosphorous	: 0.05% maximum	G24	:	700 – 1200
		G34	:	1000 – 1400
		Pack Size	:	25 kg bag

Physical Data

Shape	: Angular
Colour	: Silver/ Black Metallic
Apparent density	: Not less than 7g/cc
Hardness	: 40 – 50 HRC (390 – 510 VPN)

Turbogrit is a non-toxic and non-hazardous product. No special disposal precautions are required for the product once it has been used for blast finishing purposes. However, contamination from a specific application or process must also be considered prior to disposal

See Guyson MSDS reference 24 for all other details

Guyson International Limited
Snaygill Industrial Estate Keighley Road ▪ SKIPTON ▪ North Yorkshire ▪ BD23 2QR

Tel: +44 (0) 1756 799911 ▪ E-Mail: info@guyson.co.uk ▪ Website: www.guyson.co.uk

Manual Blast Systems ▪ Semi/Fully Automated Blast System ▪ Robotic Blast Systems
Ultrasonic Baths and Tanks ▪ Multi-Stage Aqueous Ultrasonic Systems ▪ Mono and Co-Solvent Cleaning Systems
Rotary Basket Spray Wash Systems ▪ Spare Parts / Blast Media ▪ Service

