



Received:04/04/2016	Completed:04/29/2016	Letter: C	CT	P.O.#:	Test Report #:	3-12797-0-
---------------------	----------------------	-----------	----	--------	----------------	------------

Client's Identification	Style: Hush. Composition: 80% Polyester, 20% Viscose. Weight: 325 g/lm. Product End Use: Screens.
-------------------------	---

Tested For: Bente Ellingsoe, Quality Department Gabriel A/S Hjulmagervej 55 DK-9000 Aalborg, Denmark	Key Test: ASTM E 84/ACT Tel: 011-45-9630-3100 Fax: 011-45-9811-6125	1195 Ext:
--	---	------------------

Test Category: Tunnel Test Specifier: ACT NTR 8/15 LE 2015; V 08/15
 PC: ME dl/SM

TEST PERFORMED: ASTM E 84 - Standard Test Method for Surface Burning Characteristics of Building Materials * --

As cited by the ACT Voluntary Performance Guidelines (January 2015)

APPROXIMATE THICKNESS OF SPECIMEN (as measured by Govmark): 0.088"

PRODUCT CATEGORY:

- Direct Glue Wallcoverings
- Wrapped Panels & Upholstered Walls
- Other Products: _____

* NOTE: Textile or expanded vinyl wallcoverings classified by this procedure are limited to use in sprinklered areas in certain public occupancies. If textile or expanded vinyl wallcoverings are used in non-sprinklered areas, the NFPA 265 corner fire test is mandated.

For other interior finish products in non-sprinklered areas, a room corner fire test also applies. This would be NFPA 286.

SPECIMEN MOUNTING:

- Self Supporting: The test specimen, the face of which was 23" ± 1" x 24', was such that it remained in position in the tunnel during the fire test, and no additional support was required.
- Adhered to IRC: The test specimen was bonded to three 1/4" IRC (Inorganic Reinforced Cement) boards (a cement asbestos substitute) to form a test specimen the face of which was 23" ± 1" x 24'.
- Adhered to Gypsum: The test specimen was adhered to 5/8" thick Type X gypsum board, to form a test specimen the face of which was 23" ± 1" x 24'.
- Unadhered: The 23" ± 1" x 24' specimen was not adhered to any substrate. Instead, it was laid over a 2" hexagonal wire mesh screen and 1/4" rods.
- Other: _____



Received:04/04/2016 Completed:04/29/2016 Letter: C CT P.O.#: Test Report #: 3-12797-0-

Client's Identification Style: Hush. Composition: 80% Polyester, 20% Viscose. Weight: 325 g/lm. Product End Use: Screens.

Tested For: **Bente Ellingsoe, Quality Department** Key Test: ASTM E 84/ACT 1195
 Gabriel A/S
 Hjulmagervej 55 Tel: 011-45-9630-3100 Ext:
 DK-9000 Aalborg, Denmark Fax: 011-45-9811-6125

RESULTS:

Flame Spread Index: 15
 Smoke Developed: 10

ACCEPTANCE CRITERIA:

	Flame Spread Index	Smoke Developed
Class A	0 - 25	450 or less

NOTE: Class A is also known as Class 1, and may be so specified in some Codes.

CONCLUSION: Based on the above Results and Acceptance Criteria the item tested:


Complies; Does not comply

REMARKS: None

DATA SUMMARY:

Time to Ignition: 01.05 minutes
 Maximum Flame Spread "Distance": 03.79 feet
 Maximum Flame Spread "Time": 04.20 minutes

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified above.


 AUTHORIZED SIGNATURE
 GOVMARK
 CT/pm

qib

Douglas W. Lipp

MAY 03 2016