

PRIMO CHOICE: TECHNICAL SPECIFICATION



CONSTRUCTION

MACHINE GAUGE

PILE HEIGHT

TUFT DENSITY

PILE WEIGHT

TOTAL CARPET WEIGHT

CARPET THICKNESS

WIDTH

ROLL SIZE

BS 4223/ISO 8543

BS 4223/ISO 8543

BS 4223/ISO 8543

BS 4223/ISO 8543

BS 4051/ISO 1765

BS

SUPER

Tufted Cut Pile Carpet

1/10th Cut Pile

6.7 mm

139,500 tufts/m²

1,152 gms/m²

34 oz/yd²

1,899 gms/m²

10.2 mm

4 & 5 metre

Standard 25m or 30m

(Special sizes can be supplied,
please allow extra time for delivery)

ELITE

Tufted Cut Pile Carpet

1/10th Cut Pile

8.6 mm

162,750 tufts/m²

1,627 gms/m²

48 oz/yd²

2,407 gms/m²

11.9 mm

4 & 5 metre

Standard 25m or 30m

(Special sizes can be supplied,
please allow extra time for delivery)



COMPOSITION

PILE CONTENT

PRIMARY BACKING

SECONDARY BACKING

BS 4407

100% Excellon Polypropylene

Woven Polypropylene

Woven Secondary

100% Excellon Polypropylene

Woven Polypropylene

Woven Secondary



PERFORMANCE

SUITABILITY

WIRA ABRASION TEST

STATIC LOADING

DYNAMIC LOADING

TUFT ANCHORAGE

Heavy Domestic

Exceeds 50,000 Rubs

18% Thickness Loss after 24 hrs recovery

41.5% Thickness Loss after 1,000 impacts

Above 1kg

Extra Heavy Domestic / Medium Contract

Exceeds 50,000 Rubs

16.8% Thickness loss after 24 hrs recovery

31.3% Thickness loss after 1,000 impacts

Above 1kg



COLOUR FASTNESS

LIGHT FASTNESS

WET FASTNESS

SHAMPOO FASTNESS

BS 1006

BS 1006

BS 1006

4/5 on all colours

5 on all colours

5 on all colours

4/5 on all colours

5 on all colours

5 on all colours



THERMAL VALUE

TOG VALUE

BS 4745/ISO 5085-1

1.0 Tog

1.2 Tog



FLAMMABILITY

METHENAMINE PILL TEST

CE

Pass - Low radius of ignition

Efl

Pass - Low radius of ignition



CHEMICAL IMPACT

FORMALDEHYDE

CE

E1



BIOLOGICAL ATTACK

MOTH / INSECT RESISTANT

Insect and Rot Proof

Insect and Rot Proof

GENERAL INFORMATION

Installation - In all contract locations an 'all-over' stick down method is recommended to BS 5325 (1983). If underlay is required it should be of a firm and unyielding type and where installed in larger contract areas the carpet should be power stretched. For quantity orders requiring colour matching, please state at time of ordering.

Maintenance - To maintain your carpet's appearance it is recommended that it is vacuumed at least three times per week, to remove particles of dirt and dust. An upright vacuum with beater bar and brush is recommended for use with cut pile carpets. Please note, over time, regular foot traffic will flatten the pile surface in the main walkways, causing areas of differential wear.

These areas will appear lighter or shaded in comparison to the less frequently use parts. This shading / tracking or flattening happens to all carpets with a pile surface and as such is not accepted as the basis for any complaint. Similarly Pile Reversal (or watermarking) is a phenomenon that can affect all cut pile carpets and as such is not accepted as a manufacturing fault.

Matching - This sample may not be from the same production batch as current stock and therefore should be used as a guide and not as an exact match. Equally matching between 5 metre and 4 metre widths cannot be guaranteed.

Important - Minimum order length is 1.5 metres.