



Latexplan Trade Fast



Two-part rapid curing smoothing/levelling compound. Moisture tolerable. Suitable for use on most old adhesive residues including bitumen

WHERE TO USE

Latexplan Trade Fast is used for levelling and smoothing differences in thicknesses of 3 to 10 mm (in one application) where rapid installation of all types of floor coverings is required on new and existing substrates.

Latexplan Trade Fast is suitable for high intensity, wheelchair traffic and chairs with castors. Can also be used over most old adhesive residues including bitumen.

Latexplan Trade Fast is also suitable for use with under floor heating.

Some application examples

Smoothing concrete floors, sand:cement screeds, MAPEI **Mapecem** and MAPEI **Topcem** screeds. For smoothing over existing flooring in concrete, terrazzo, ceramic, porcelain tiles and natural stone (after applying a suitable primer if required).

TECHNICAL CHARACTERISTICS

Latexplan Trade Fast is a two-part cement based smoothing compound consisting of a grey powder (part A) containing special cements, graded silica sands and additives to be mixed with a synthetic rubber latex (part B).

Latexplan Trade Fast can receive foot traffic after approximately 60 minutes and is ready to install floor coverings after 2½-3 hours depending on the thickness and ambient temperature.

Latexplan Trade Fast has a very low odour making it

suitable for use in confined and inhabited areas, where working and/or occupation must be maintained.

Latexplan Trade Fast should not be mixed with any additional latex liquid or any water.

Latexplan Trade Fast is moisture tolerable and suitable for use under MAPEI damp proof membranes.

Preparation

The sub floor must be clean, structurally sound, and free from grease, oil, paint, and plaster residues, surface contamination, including surface hardeners, water softenable adhesives, loosely applied materials, and additives that may compromise the bond. Adhesive residue must be checked to confirm they are not water softenable and that they are hard, solid and are suitably strong enough to receive a smoothing/levelling compound.

Priming (75% R.H. or below)

On highly porous and absorbent surfaces, a coat of primer prior to the application of smoothing compounds etc will reduce pin holes and air bubbles on the subsequent compounds above.

Eco Prim T is suitable for absorbent substrates and surfaces. For non porous surfaces use **Eco Prim Grip**.

For using surface damp proof membrane, ensure primer is not applied prior to the application of the membrane but above it.

When applying Latexplan Trade Fast above cured

TECHNICAL DATA (typical values)	
PRODUCT IDENTITY	
PART A	
Consistency:	fine powder
Colour:	grey
Dry solids content (%):	100
Bulk Density (kg/m ³):	1,400
Flammable:	no
PART B	
Consistency:	runny liquid
Colour:	white
Dry solids content (%):	15
Bulk density (kg/m ³):	1,050
Flammable:	no
COMPOSITION AND PROPERTIES OF THE MIXTURE	
Mixing ratio:	4 kg of Latexplan Trade Fast liquid with 20 kg of Latexplan Trade Fast powder
Thickness per coat:	3 mm to 10 mm
Density of mix (kg/m ²):	2,000
Application temperature range (°C):	5-35
Workability (at +23°C):	20'
Setting time:	30'
Set to light foot traffic:	60 minutes
Time before laying floorcovering:	2 hrs 30 minutes to 3 hours
FINAL PERFORMANCE DATA	
Compressive strength (N/mm ²):	
– after 1 day:	15
– after 7 days:	25
– after 28 days:	32
Flexural strength (N/mm ²):	
– after 1 day:	3
– after 7 days:	5
– after 28 days:	7
Resistance to abrasion after 28 days:	2 g

MAPEI surface applied membranes, in all cases the membrane must be primed.

Mixing

Mix 20 kg of **Latexplan Trade Fast** part A powder into 4 litres of **Latexplan Trade Fast** part B liquid. The **Latexplan Trade Fast** part B liquid container should be shaken and poured into a clean mixing container. The **Latexplan Trade Fast** part A powder is then added gradually whilst continually stirring with a mixing paddle attached to a slow-speed drill. The mixed product has a working time of approximately 10-15 minutes at +23°C.

Do not add more latex liquid or water to the mix once it has begun to set.

Do not over mix the products as this will cause excessive heat and cause the mixed product to cure too quickly.

Application

The mixed product is poured onto the prepared subfloor and spread with a smooth edged trowel to the required thickness in one operation. Alternatively the use of a spiked roller will ensure a smooth even finish that will not require any further attention prior to the floor coverings being installed.

Do not over-trowel the product once it has been placed on to the sub floor.

The correct mix permits thicknesses from 3 mm to 10 mm per application, ensure a minimum 3 mm thickness is applied to provide the optimum absorption for the adhesive (apply at a minimum floor temperature of above +5°C).

Drying

At normal temperatures **Latexplan Trade Fast** will take light foot traffic after 60 minutes and will accept bonded floor coverings after 2½-3 hours.

Cleaning Equipment

All tools and mixing containers should be washed and cleaned immediately after use before the material hardens.

COVERAGE

One unit (part A + part B) will cover approximately 4.5-5 m² at 3 mm thickness.

STORAGE

Latexplan Trade Fast part A has a storage life of approximately 12 months if stored in dry conditions.

Latexplan Trade Fast part A conforms with the conditions of Annex XVII to Regulation (EC) N° 1907/2006 (REACH) - All. XVII, item 47.

Latexplan Trade Fast part B has a storage life of approximately 24 months if stored in dry conditions and protected from frost.

SAFETY INSTRUCTIONS FOR PREPARATION AND APPLICATION

Latexplan Trade Fast component A contains cement that when in contact with sweat or other body fluids causes an irritant alkaline reaction and allergic reactions to those predisposed. It can cause damage to eyes. In case of contact with eyes or skin wash immediately with plenty of water and seek medical attention.

Latexplan Trade Fast component B is not considered as dangerous according to the current regulation regarding the classification of mixtures.

We recommend the use of protective gloves and goggles and to take the usual precautions for handling chemical products. For further and complete information about the safe use of our product please refer to the latest version of our Material Safety Data Sheet.

PRODUCT FOR PROFESSIONAL USE.

N.B.

Whilst we try to ensure that any advice, recommendations or information given in our literature is accurate and correct, we have no control over the circumstances in which our product is used. It is therefore important that the end users satisfy themselves that the product and conditions are suitable for the envisaged application.

No warranty can be given or responsibility accepted other than, that the product supplied by us will meet our written specification.

End users should ensure that our latest product data and safety information sheets have been consulted prior to use.

Please refer to the current version of the Technical Data Sheet, available from our website www.mapei.co.uk

LEGAL NOTICE

The contents of this Technical Data Sheet ("TDS") may be copied into another project-related document, but the resulting document shall not supplement or replace requirements per the TDS in force at the time of the MAPEI product installation.

The most up-to-date TDS can be downloaded from our website www.mapei.co.uk.

ANY ALTERATION TO THE WORDING OR REQUIREMENTS CONTAINED OR DERIVED FROM THIS TDS EXCLUDES THE RESPONSIBILITY OF MAPEI.

All relevant references for the product are available upon request and from www.mapei.co.uk



**Latexplan
Trade Fast**



BUILDING THE FUTURE

Any reproduction of texts, photos and illustrations published here is prohibited and subject to prosecution

4019-7-2017 (UK)