

# NORR 12"x24" 24"x24"



Vit RR 01



Vit RR 01



Vit RR 01 + Grä RR 02



Grä RR 02 + Svart RR 03



Svart RR 03 + Vit RR 01

## Vit (Dark White)




24"x24"




12"x24"

## Gra (Grey)




24"x24"




12"x24"

## Svart(Anthracite)





24"x24"



12"x24"

## Mosaic 1"x 2"












12"x12"

## Battiscopa



3"x24"

	 12"x24"	 24"x24"	 Mosaic 12"x12"	 Battiscopa 3"x24"		
Thickness	E 2/8"					
Surface	LBS/CTN	LBS/CTN	LBS/CTN	LBS/CTN	NAT	
 Gross weight per box	52.096	52.096	52.096	52.096	-	-
 Pieces for box	6	6	3	3	6	10
 Sf. box	11.6208	11.6208	11.6208	11.6208	-	-
 Boxes / full pallet	40	40	40	40	-	-
 Sf. / pallet	464.832	464.832	464.832	464.832	-	-



## STANDARD EN 14411 - G

TECHNICAL DATA	STANDARD	INTERNATIONAL STANDARDS EN 14411 - G	AVERAGE VALUE	
SURFACE FLATNESS	EN ISO 10545-2	± 0,5% MAX (± 2,0 mm MAX)	COMPLYING	
WATER ABSORPTION	EN ISO 10545-3	≤ 0,5%	0,03%	
FLEXION RESISTANCE	EN ISO 10545-4	S ≥ 700 N (< 7,5 mm) S ≥ 1.300 N (> 7,5 mm) R ≥ 35 N/mm².	S 3.131 N R 54,3 N/mm²	
FROST RESISTANCE	EN ISO 10545-12	PASS ACCORDING EN ISO 10545-1	NO DAMAGE	
RESISTANCE TO STAINS	EN ISO 10545-14	DECLARED VALUE	5	
SKID RESISTANCE			NAT	ST
	DM. 236/89 BCRA	> 0,40	> 0,40	> 0,40
	ASTM Wet and Dry	> 0,60	> 0,60	> 0,60
	DIN 51130	-	R10	R11
	ENV 12633	≥ CL1	CL2	CL3