

Laminate Flooring Technical parameters

Technial Specification	Test Standard	Test result
Density (g/cm ³)	≥ 0. 8	0, 88
Surface Wear ®	≥ 4500 turns	6000 turns
Formaldehyde Release (mg/100g)	≤ 6	4, 86
Modulus of Rupture (Mpa)	≥ 35	42, 8
Internal Bond Strength	≥ 1. 3	1, 54
Water Absorption Thickness Swell (%)	≤ 10	8, 2
Moisture Content (%)	≤ 4- 7	5, 9