










CARACTERÍSTICAS TÉCNICAS  
TECHNICAL FEATURES

**PORCEMALL**



<b>KENDAL</b>	
FORMATO/ <i>FORMAT</i>	20x120
ESPESOR/ <i>THICKNESS</i> (mm)	10,5
PRODUCTO/ <i>PRODUCT</i>	PORCELANICO/ <i>PORCELAIN</i>
TIPO/ <i>KIND</i>	ESMALTADO/ <i>GLAZED</i>
GRUPO/ <i>GROUP</i>	Bla - GL

NORMA APLICABLE EN 14411 ANEXO G  
APPLICABLE STANDARD ISO 13006 ANNEX G

ENSAYOS/ <i>TESTS</i>		RESULTADOS/ <i>RESULTS</i>	
	UNE-EN ISO 10545-2 DIMENSIONES Y ASPECTO SUPERFICIAL <i>UNE-EN ISO 10545-2 DIMENSIONS AND SURFACE QUALITY</i>	DIMENSIONES <i>DIMENSIONS</i>	CUMPLE CON LA NORMA <i>COMPLIES WITH THE STANDARD</i>
	UNE-EN ISO 10545-3 ABSORCIÓN DE AGUA <i>UNE-EN ISO 10545-3 WATER ABSORPTION</i>	VALOR MEDIO (%) <i>AVERAGE VALUE (%)</i>	≤ 0,5 %
	UNE-EN ISO 10545-4 RESISTENCIA A LA FLEXIÓN <i>UNE-EN ISO 10545-4 MODULUS OF RUPTURE</i>	FUERZA DE ROTURA <i>BREAKING STRENGTH (N)</i>	1.600 - 2.400 N
		RESISTENCIA A LA FLEXIÓN <i>MODULUS OF RUPTURE (N/mm<sup>2</sup>)</i>	35 - 45 N/mm <sup>2</sup>
	UNE-EN ISO 10545-9 RESISTENCIA AL CHOQUE TÉRMICO <i>UNE-EN ISO 10545-9 THERMAL RESISTANCE</i>	RESULTADO <i>RESULT</i>	RESISTE <i>RESISTS</i>
	UNE-EN ISO 10545-11 RESISTENCIA AL CUARTEO <i>UNE-EN ISO 10545-11 CRAZING RESISTANCE</i>	RESULTADO <i>RESULT</i>	RESISTE <i>RESISTS</i>
	UNE-EN ISO 10545-12 RESISTENCIA A LA HELADA <i>UNE-EN ISO 10545-12 FROST RESISTANCE</i>	RESULTADO <i>RESULT</i>	RESISTE <i>RESISTS</i>
	UNE-EN ISO 10545-13 RESISTENCIA QUÍMICA <i>UNE-EN ISO 10545-13 CHEMICAL RESISTANCE</i>	COLORURO AMÓNICO <i>AMMONIUM CHLORIDE</i> 100 g/l HIPOCLORITO SÓDICO <i>SODIUM HYPOCHLORITE</i> 20 mg/l	A
		ÁCIDO CLORHÍDRICO <i>HYDROCHLORIC ACID</i> 3% ÁCIDO CÍTRICO <i>CITRIC ACID</i> 100 g/l HIDRÓXIDO POTÁSICO <i>POTASSIUM HYDROXYDE</i> 30 g/l	CUMPLE CON LA NORMA <i>COMPLIES WITH THE STANDARD</i>
	UNE-EN ISO 10545-14 RESISTENCIA A LAS MANCHAS <i>UNE-EN ISO 10545-14 STAIN RESISTANCE</i>	ÓXIDO VERDE EN ACEITE LIGERO <i>GREEN AGENT IN LIGHT OIL</i>	5
		SOLUCIÓN ALCOHÓLICA DE YODO <i>IODINE SOLUTION IN ALCOHOL</i>	5
		ACEITE DE OLIVA <i>OLIVE OIL</i>	5

OBSERVACIONES:

VºBº LABORATORIO:



**PORCEMALL**